

Title (en)
CORROSION AND WEAR-RESISTANT CHILL CASTING

Title (de)
KORROSIONS- UND VERSCHLEISSBESTÄNDIGER HARTGUSS

Title (fr)
PRODUIT MOULE EN COQUILLE RESISTANT A LA CORROSION ET A L'USURE

Publication
EP 0750686 B1 19980610 (DE)

Application
EP 95912186 A 19950302

Priority

- DE 4409278 A 19940318
- EP 9500759 W 19950302

Abstract (en)
[origin: US5795540A] PCT No. PCT/EP95/00759 Sec. 371 Date Sep. 17, 1996 Sec. 102(e) Date Sep. 17, 1996 PCT Filed Mar. 2, 1995 PCT Pub. No. WO95/25826 PCT Pub. Date Sep. 28, 1995A corrosion and wear-resistant chill cast part is formed from an iron composition comprising from 26 to 36 percent Cr; 0 to 10 percent Ni; 2 to 6 percent Mo; 0 to 3 percent Cu; 0 to 0.2 percent N; 0 to 1.5 percent Si; 0 to 1.5 percent Mn; 4 to 9 percent V; and 1.4 to 1.9 percent C. All percents are by weight of the total composition. The remainder of the composition is Fe and impurities.

IPC 1-7
C22C 37/08; **C22C 38/36**

IPC 8 full level
C22C 37/00 (2006.01); **C22C 37/06** (2006.01); **C22C 37/08** (2006.01); **C22C 38/24** (2006.01); **C22C 38/36** (2006.01)

CPC (source: EP US)
C22C 37/08 (2013.01 - EP US); **C22C 38/24** (2013.01 - EP US)

Cited by
DE102020003847A1; WO2021259658A1; EP3929444A1; DE102020003854A1

Designated contracting state (EPC)
AT BE CH DE ES FR GB IT LI NL PT SE

DOCDB simple family (publication)
US 5795540 A 19980818; AT E167238 T1 19980615; AU 1947795 A 19951009; AU 678107 B2 19970515; BR 9506610 A 19970909; CN 1044494 C 19990804; CN 1143982 A 19970226; DE 4409278 A1 19950921; DE 59502510 D1 19980716; EP 0750686 A1 19970102; EP 0750686 B1 19980610; ES 2120187 T3 19981016; JP H10500449 A 19980113; WO 9525826 A1 19950928

DOCDB simple family (application)
US 71639196 A 19960917; AT 95912186 T 19950302; AU 1947795 A 19950302; BR 9506610 A 19950302; CN 95192063 A 19950302; DE 4409278 A 19940318; DE 59502510 T 19950302; EP 9500759 W 19950302; EP 95912186 A 19950302; ES 95912186 T 19950302; JP 52432895 A 19950302