

Title (en)

High strength low thermal expansion alloy

Title (de)

Hochfeste Legierung mit niedrigem Ausdehnungskoeffizient

Title (fr)

Alliage à haute résistance et à coefficient d'expansion thermique faible

Publication

EP 0765950 B1 20011017 (EN)

Application

EP 96306099 A 19960821

Priority

- US 51967895 A 19950825
- US 69648796 A 19960814

Abstract (en)

[origin: EP0765950A1] The alloy of the invention provides a low coefficient of thermal expansion alloy having a CTE of about 4.9×10^{-6} m/m/ DEG C or less at 204 DEG C and a relatively high strength. The alloy contains about 40.5 to about 48 nickel, about 2 to about 3.7 niobium, about 0.75 to about 2 titanium, about 0 to about 1 aluminum, about 3.7 or less total niobium plus tantalum and a balance of iron and incidental impurities. Alloys of the invention may be aged to a Rockwell C hardness of at least about 30.

IPC 1-7

C22C 38/08

IPC 8 full level

C22C 30/00 (2006.01); **C22C 38/00** (2006.01); **C22C 38/08** (2006.01); **C22C 38/14** (2006.01); **C22C 38/60** (2006.01)

CPC (source: EP)

C22C 38/08 (2013.01)

Designated contracting state (EPC)

DE ES FR GB

DOCDB simple family (publication)

EP 0765950 A1 19970402; EP 0765950 B1 20011017; EP 0765950 B2 20100120; DE 69615977 D1 20011122; DE 69615977 T2 20020404;
DE 69615977 T3 20100506; ES 2161983 T3 20011216; JP H09165653 A 19970624

DOCDB simple family (application)

EP 96306099 A 19960821; DE 69615977 T 19960821; ES 96306099 T 19960821; JP 22412496 A 19960826