

Title (en)

COATING COMPOSITION, PROCESS FOR PREPARING THE COMPOSITION, AND PROCESS FOR PREPARING DISPERSION OF INORGANIC OXIDE SOL

Title (de)

ÜBERZUGSZUSAMMENSETZUNG, VERFAHREN ZU IHRER HERSTELLUNG UND VERFAHREN ZUR HERSTELLUNG EINER ANORGANISCHEN OXIDSOLDISPERSION

Title (fr)

COMPOSITION DE REVETEMENT, PROCEDE D'ELABORATION DE CETTE COMPOSITION ET PROCEDE D'ELABORATION D'UNE DISPERSION DE SOL D'OXYDE INORGANIQUE

Publication

EP 0768351 B1 20010919 (EN)

Application

EP 96912222 A 19960424

Priority

- JP 9601114 W 19960424
- JP 12899895 A 19950428
- JP 34699095 A 19951214

Abstract (en)

[origin: EP0768351A1] A coating composition which comprises: (A) a resin having a glass transition temperature of 50 to 120 DEG C., a number average molecular weight of 2,000 to 100,000, a hydroxyl value of 50 to 150 mgKOH/g and an acid value of 1 to 25 mgKOH/g, which is produced by copolymerizing 10 to 90 percent by weight of (a) a (meth) acrylic acid ester of an alkyl alcohol of 1 to 12 carbon atoms, 10 to 50 percent by weight of (b) a polymerizable double bond-containing and hydroxyl group-containing monomer, 0.1 to 10 percent by weight of (c) a polymerizable double bond-containing and carboxyl group-containing monomer, 0 to 20 percent by weight of (d) styrene, 0 to 20 percent by weight of (e) acrylonitrile and 0 to 10 percent by weight of (f) other polymerizable double bond-containing monomer, (B) at least one compound selected from the group consisting of a polyisocyanate compound having two or more isocyanate groups and/or blocked isocyanate groups in the molecule and an aminoplast resin, (C) a dispersing component of at least one inorganic oxide sol selected from the group consisting of an aluminium oxide sol, a silica sol, a zirconium oxide sol and an antimony oxide sol, wherein an amount of a nonvolatile matter of ingredient (C) is 5 to 60percent by weight based on a total nonvolatile matter of ingredient (A), ingredient (B) and ingredient (C), and a process for preparing a coating composition which comprises: preparing the resin (A), adding the dispersing component of an inorganic oxide sol (C) into a polymerization liquid containing the resin (A) after finishing of the copolymerization of the resin (A) to produce a organic-inorganic composite, and then mixing the organic-inorganic composite and ingredient (b). The coating compositions give the cured films having excellent weathering resistance, light resistance, stain resistance, stain-removing property, chemical resistance, moisture resistance and appearance and is excellent in environment friendliness and safety.

IPC 1-7

C09D 133/06; **C09D 133/14**; **C09D 175/04**; **B01J 13/00**

IPC 8 full level

C08G 18/62 (2006.01); **C09D 133/06** (2006.01); **C09D 175/04** (2006.01); **C08L 61/20** (2006.01)

CPC (source: EP US)

C08G 18/6254 (2013.01 - EP US); **C09D 133/066** (2013.01 - EP US); **C09D 175/04** (2013.01 - EP US); **C08L 61/20** (2013.01 - EP US); **Y10T 428/2995** (2015.01 - EP US)

Cited by

EP1085136A4; US6020419A; EP0805186A4; US7229672B2; DE10208905A1; EP1388581A1; US6025455A; DE10208905B4; US7179513B2; US7906179B2; WO03064557A1; WO2007009557A1; WO2006099375A1; US7282272B2; US7547476B2; US7427438B2; US7326448B2; US8025934B2; US8034421B2; US8241755B2; US6291078B1; US7384697B2; US9376544B2; EP1631523B1

Designated contracting state (EPC)

DE GB

DOCDB simple family (publication)

EP 0768351 A1 19970416; **EP 0768351 A4 19980610**; **EP 0768351 B1 20010919**; CN 1071366 C 20010919; CN 1152328 A 19970618; CN 1163559 C 20040825; CN 1332212 A 20020123; DE 69615304 D1 20011025; DE 69615304 T2 20020502; JP 3298891 B2 20020708; US 6022919 A 20000208; US 6376559 B1 20020423; WO 9634063 A1 19961031

DOCDB simple family (application)

EP 96912222 A 19960424; CN 00134825 A 19960424; CN 96190399 A 19960424; DE 69615304 T 19960424; JP 53235396 A 19960424; JP 9601114 W 19960424; US 36184799 A 19990727; US 75806296 A 19961127