

Title (en)  
Ligth structural steel and its application

Title (de)  
Leichtbaustahl und seine Verwendung

Title (fr)  
Acier pour des éléments de construction et son application

Publication  
**EP 0889144 A1 19990107 (DE)**

Application  
**EP 98109813 A 19980529**

Priority  
DE 19727759 A 19970701

Abstract (en)  
The invention relates to a high-quality, cold-formable, ultra-resistant austenitic light constructional steel having particularly good deep-draw qualities, with a tensile strength of up to 1,100 MPa in addition to TRIP and TWIP qualities. The invention also relates to the use of said steel in body work components reinforcing structural components, cryogen containers and piping.

Abstract (de)  
Die Erfindung betrifft einen gut kaltumformbaren, insbesondere gut tiefziehfähigen, ultrahochfesten austenitischen Leichtbaustahl mit einer Zugfestigkeit bis 1100 MPa und mit TRIP- und TWIP-Eigenschaften sowie seine Verwendung für Karosserieblechteile, versteifende Strukturkomponenten und Cryogen-Behälter und Rohrleitungen. Der Stahl hat die chemische Zusammensetzung (in Masse-%): 1 bis 6% Si, 1 bis 8% Al mit (Al + Si) <= 12%, 10 bis 30% Mn, Rest Eisen, einschließlich üblicher Stahlbegleitelemente.

IPC 1-7  
**C22C 38/04; C22C 38/06; C22C 38/02**

IPC 8 full level  
**C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01)

CPC (source: EP US)  
**C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US)

Citation (search report)

- [A] US 5348701 A 19940920 - OHDAKE TAKAYUKI [JP], et al
- [X] R. WANG UND F. BECK: "New stainless steel without nickel or chromium for marine applications", METAL PROGRESS, vol. 123, no. 4, March 1983 (1983-03-01), pages 72 - 76, XP002081701
- [A] PATENT ABSTRACTS OF JAPAN vol. 016, no. 304 (C - 0959) 6 July 1992 (1992-07-06)
- [T] O. GRÄSSEL ET AL.: "Phase transformations and mechanical properties of Fe-Mn-Si-Al TRIP steels", J.PHYS. IV, vol. 7, no. C5, November 1997 (1997-11-01), pages 383 - 388, XP002081702

Cited by  
DE102007061062A1; WO2005061152A1; CN102230115A; CN110684928A; DE102007061062B4; RU2476604C2; EP2749659A1; DE102015111680A1; CN107848012A; US8778097B2; WO2014097184A2; DE102008005806A1; US10273556B2; WO2006048034A1; WO2006111464A1; WO2013124283A1; WO2007062702A1; DE102009003598A1; US9856542B2; WO2020169764A1; US9677146B2; WO2017148892A1; US11078555B2; US7806165B2; WO2012081871A2; US9738958B2; US8444743B2; US9206698B2; WO2009076923A2

Designated contracting state (EPC)  
AT BE ES FR GB IT LU NL PT SE

DOCDB simple family (publication)  
**EP 0889144 A1 19990107; EP 0889144 B1 20020717; EP 0889144 B8 20091118**; AT E220731 T1 20020815; DE 19727759 A1 19990107; DE 19727759 C2 20000518; ES 2179400 T3 20030116; JP 2002507251 A 20020305; US 6387192 B1 20020514; WO 9901585 A1 19990114

DOCDB simple family (application)  
**EP 98109813 A 19980529**; AT 98109813 T 19980529; DE 19727759 A 19970701; EP 9804044 W 19980701; ES 98109813 T 19980529; JP 50632799 A 19980701; US 46204299 A 19991229