

Title (en)
THIN, FINE PORED METAL LAYER

Title (de)
DÜNNE, FEINPORIGE METALLSCHICHT

Title (fr)
COUCHE METALLIQUE MINCE A MICROPORES

Publication
EP 0977909 A1 20000209 (DE)

Application
EP 98916815 A 19980227

Priority
• DE 9800594 W 19980227
• DE 19716595 A 19970421

Abstract (en)
[origin: WO9848077A1] The invention relates to a metal layer with open porosity and with a maximum thickness of 500 μ m, whereby the diameter of the through pores is at most a twelfth of the thickness of the layer. In order to produce a metal layer with open porosity, a suspension containing metal powder, dispersant as well as substances for adjusting the viscosity is deposited in layers on a support, dried and then sintered. The thickness of the suspension layer deposited on the support must be such that the thickness of the metal layer after sintering is at least three times the diameter of the metal powder.

IPC 1-7
C23C 24/08

IPC 8 full level
B22F 3/22 (2006.01); **C23C 24/08** (2006.01)

CPC (source: EP)
B22F 5/106 (2013.01); **B22F 7/002** (2013.01); **B22F 2998/10** (2013.01); **B22F 2999/00** (2013.01)

C-Set (source: EP)
1. **B22F 2998/10 + B22F 3/22 + B22F 3/10**
2. **B22F 2999/00 + B22F 3/22 + B22F 3/06**

Cited by
US7306753B2

Designated contracting state (EPC)
AT CH DE FR GB IT LI SE

DOCDB simple family (publication)
WO 9848077 A1 19981029; AT E219166 T1 20020615; DE 19716595 C1 19980903; DE 19758454 A1 19981022; DE 59804429 D1 20020718; EP 0977909 A1 20000209; EP 0977909 B1 20020612

DOCDB simple family (application)
DE 9800594 W 19980227; AT 98916815 T 19980227; DE 19716595 A 19970421; DE 19758454 A 19970421; DE 59804429 T 19980227; EP 98916815 A 19980227