

Title (en)

Method and device for improving the cross-machine shrinkage profile in a paper machine

Title (de)

Verfahren und Vorrichtung zur Verbesserung des Schrumpfungs-Querprofils in einer Papiermaschine

Title (fr)

Procédé et dispositif pour améliorer le profil transversal du rétrécissement dans une machine à papier

Publication

EP 0995834 A1 20000426 (DE)

Application

EP 99112905 A 19990705

Priority

DE 19843729 A 19980924

Abstract (en)

[origin: EP1323862A1] To maintain the lateral profile of a running paper or cardboard web, the lateral shrinkage profile is adjusted during the formation process. The variations are through alterations in the fiber suspension composition locally to affect sections across the web width, using different proportions of suspension components with different shrinkage behaviors. <??>The shrinkage is increased at a section zone by a raised feed of fibers and/or other matter with a high shrinkage, or replacing fibers with fibers which shrink more strongly. The shrinkage is reduced by increasing the fiber feed of fibers with a low shrinkage character and/or other matter which shrinks less or replacing the fibers with the suspension containing fibers with lower shrinkage. The composition of the fiber suspension is adjusted at the stock inlet and/or the wet web section of the machine. Two flows of fiber suspension are prepared, to be mixed together at sections of the stock inlet to set the lateral shrinkage, while the lateral weight profile of the web is modified by the controlled flow of diluting water in sections across the web width. The fibers with a high shrinking tendency are long fibers and vice versa, very open fibers and vice versa, highly chopped or ground fibers and vice versa. The added matter to increase shrinkage is carboxymethyl cellulose (CMC) and/or other matter. The added matter to reduce shrinkage is a synthetic resin and/or wet strength agents and/or the like. The lateral weight profile of the web is measured, and the control values are determined to match the web weight in sections (N) across the web width together with a nominal profile for the operation of actuators (7). The shrinkage is computed by on-line mapping of the lateral weight profile, and the control values to set the shrinkage in sections (M) across the machine width using the nominal profile, and operate the actuators accordingly. The shrinkage with corrected values is measured, and the lateral shrinkage profile is computed by correlation between the measured values and the shrinkage. The control values are computed for sections (M) across the machine width, and the actuators are operated as appropriate. The on-line lateral weight mapping and the measurement of shrinkage with corrected values can be done together. The calculation for the lateral shrinkage profile is through correlation between the measured values and the shrinkage, and the weighted lateral shrinkage profile is registered from the measured and the computed lateral shrinkage profile to give the control values for the operation of the actuators. The profile control algorithm separates the lateral weight and shrinkage profiles. The measured values of the polish and/or strength are correlated with the shrinkage. An Independent claim is included for a paper or cardboard web prodn. machine with a constant section at the stock inlet with two zones for different fiber suspensions of fiber mixtures of different shrinkage characteristics, to be fed to the stock inlet. The stock inlet has a number of mixing points, by sections, where the different fiber suspensions are fed into the flow.

Abstract (de)

Die Erfindung betrifft ein Verfahren zur Vergleichmäßigung des Eigenschaftsquerprofils einer laufenden Materialbahn aus Papier oder Karton und eine zur Durchführung des obengenannten Verfahrens geeignete Papiermaschine. Das Verfahren ist dadurch gekennzeichnet, daß das Schrumpfungsquerprofil der Materialbahn während ihres Entstehungsprozesses durch über die Breite sektionale Beeinflussung der örtlichen Zusammensetzung der Stoffsuspension durch das Verändern der Anteile der Komponenten mit unterschiedlichem Schrumpfungsverhalten vergleichmäßig wird. Die Papiermaschine zeichnet sich dadurch aus, daß der Konstante Teil mindestens zwei Bereiche aufweist, die unterschiedliche Stoffsuspensionen mit Fasergemischen mit unterschiedlichem Schrumpfungsverhalten bereitstellen, die Stoffsuspensionszuführungen vom Konstanten Teil zum Stoffauflauf mindestens zwei Stränge für die mindestens zwei unterschiedlichen Stoffsuspensionen aufweisen und im Bereich des Stoffauflaufes eine Vielzahl von sektionalen Mischstellen vorgesehen sind, welche die Stoffsuspensionen mit unterschiedlichen Schrumpfungsverhalten zusammenführen. <IMAGE>

IPC 1-7

D21F 1/08

IPC 8 full level

G01B 11/26 (2006.01); **D21F 1/06** (2006.01); **D21F 1/08** (2006.01); **D21F 7/06** (2006.01); **D21G 9/00** (2006.01); **G01B 21/32** (2006.01)

CPC (source: EP US)

D21F 1/022 (2013.01 - EP US); **D21F 1/08** (2013.01 - EP US); **D21G 9/0027** (2013.01 - EP US); **Y10S 162/11** (2013.01 - EP US)

Citation (search report)

- [A] DE 19542448 A1 19970515 - VOITH SULZER PAPIERMASCH GMBH [DE]
- [A] US 5658432 A 19970819 - HEAVEN EDWIN MICHAEL GYDE [CA], et al
- [A] WO 9619615 A1 19960627 - SIEMENS AG [DE]
- [DA] DE 4019593 A1 19920109 - VOITH GMBH J M [DE]

Cited by

CN104480769A; CN100400745C; US6564117B1; US7128808B2; WO0196660A1; WO0149931A1; DE102009028135A1; DE102011003283A1

Designated contracting state (EPC)

AT DE FI SE

DOCDB simple family (publication)

US 6303001 B1 20011016; AT E254208 T1 20031115; AT E334253 T1 20060815; CA 2283425 A1 20000324; CA 2283425 C 20081118; DE 19843729 A1 20000330; DE 59907702 D1 20031218; DE 59913719 D1 20060907; EP 0995834 A1 20000426; EP 0995834 B1 20031112; EP 1323862 A1 20030702; EP 1323862 B1 20060726; JP 2000096475 A 20000404

DOCDB simple family (application)

US 40195299 A 19990923; AT 03001610 T 19990705; AT 99112905 T 19990705; CA 2283425 A 19990923; DE 19843729 A 19980924; DE 59907702 T 19990705; DE 59913719 T 19990705; EP 03001610 A 19990705; EP 99112905 A 19990705; JP 27113499 A 19990924