

Title (en)
MINERAL FIBRE INSULATION

Title (de)
MINERALFASER FÜR ISOLATIONSZWECKE

Title (fr)
ISOLATION A FIBRE MINERALE

Publication
EP 1003694 A1 20000531 (EN)

Application
EP 98936400 A 19980630

Priority
• EP 9803979 W 19980630
• GB 9717486 A 19970818

Abstract (en)
[origin: WO9908969A1] Pipe sections or external roof or wall cladding are formed of bonded man made vitreous fibre batts wherein the fibres have a viscosity at 1400 DEG C of 10 to 170 poise and a dissolution rate at pH 4.5 of at least 20nm per day.

IPC 1-7
C03C 13/00; **C03C 13/06**

IPC 8 full level
C03C 13/00 (2006.01); **C03C 13/06** (2006.01); **E04D 3/35** (2006.01); **D01F 9/08** (2006.01); **E04B 1/78** (2006.01); **E04D 5/10** (2006.01); **F16L 59/02** (2006.01)

CPC (source: EP)
C03C 13/00 (2013.01); **C03C 13/06** (2013.01); **E04B 1/78** (2013.01); **E04D 5/10** (2013.01); **F16L 59/02** (2013.01); **C03C 2213/02** (2013.01)

Designated contracting state (EPC)
AT BE CH DE DK ES FI FR GB GR IT LI NL SE

DOCDB simple family (publication)
WO 9908969 A1 19990225; AU 8541398 A 19990308; CA 2301260 A1 19990225; CN 1267271 A 20000920; EP 1003694 A1 20000531; GB 9717486 D0 19971022; HR P980454 A2 19990430; HU P0004699 A2 20010428; HU P0004699 A3 20020228; JP 2001515006 A 20010918; PL 338833 A1 20001120; SK 1892000 A3 20000912

DOCDB simple family (application)
EP 9803979 W 19980630; AU 8541398 A 19980630; CA 2301260 A 19980630; CN 98808263 A 19980630; EP 98936400 A 19980630; GB 9717486 A 19970818; HR P980454 A 19980818; HU P0004699 A 19980630; JP 2000509662 A 19980630; PL 33883398 A 19980630; SK 1892000 A 19980630