

Title (en)

Method for producing a plating for a metal component

Title (de)

Verfahren zum Herstellen einer Panzerung für ein metallisches Bauteil

Title (fr)

Procédé de réalisation d'un blindage pour un composant métallique

Publication

EP 1088907 B1 20050810 (DE)

Application

EP 00120803 A 20000923

Priority

DE 19946650 A 19990929

Abstract (en)

[origin: EP1088907A1] Production of a cladding for a metallic component comprises forming a slip by mixing a binder solution with a starting powder containing Al and/or Cr and an additional powder containing Al, Pt, Pd or Si, where the additional powder comprises no Al when the starting powder contains exclusively Al; applying the slip to the surface to be clad; adding ceramic hard particles to the slip before or after applying the slip; drying the slip layer at a temperature of room temperature to 450 degrees C and heat treating the slip layer at 750-1250 degrees C.

IPC 1-7

C23C 10/52; C23C 10/56

IPC 8 full level

C23C 10/52 (2006.01); **C23C 10/56** (2006.01)

CPC (source: EP)

C23C 10/52 (2013.01); **C23C 10/56** (2013.01)

Cited by

EP1616979A1; EP2842662A1; DE102009008510A1; US7422769B2

Designated contracting state (EPC)

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE

DOCDB simple family (publication)

EP 1088907 A1 20010404; EP 1088907 B1 20050810; AT E301735 T1 20050815; DE 19946650 A1 20010913; DE 19946650 C2 20031127; DE 50010908 D1 20050915

DOCDB simple family (application)

EP 00120803 A 20000923; AT 00120803 T 20000923; DE 19946650 A 19990929; DE 50010908 T 20000923