

Title (en)

Production method of an aluminium alloy of AlMgSi type with Sn and Mn

Title (de)

Verfahren zur Herstellung einer Aluminiumknetlegierung des Typs AlMgSi mit Sn und Mn

Title (fr)

Méthode de production d'un alliage d'aluminium du type AlMgSi avec Sn et Mn

Publication

**EP 1098009 B1 20020703 (DE)**

Application

**EP 00121632 A 20001004**

Priority

DE 19953212 A 19991105

Abstract (en)

[origin: EP1098009A2] Aluminum wrought alloy of the AlMgSi type contains alloying additions of (in wt.%): 0.6-2.0 magnesium, 0.6-3.0 silicon, 0.6-1.5 tin, 0.4-1.0 manganese, maximum 0.25 chromium and titanium, and impurities containing maximum 0.4 iron, maximum 0.1 copper and maximum 0.2 zinc. An Independent claim is included for a process for the production of a continuously cast object made of the aluminum wrought alloy of the AlMgSi type comprising solution annealing during extrusion, quenching the extruded object and hardening.

IPC 1-7

**C22C 21/08**; **C22C 21/02**

IPC 8 full level

**C22C 21/08** (2006.01); **C22F 1/05** (2006.01); **C22C 21/00** (2006.01); **C22C 21/02** (2006.01); **C22C 21/06** (2006.01); **C22F 1/00** (2006.01)

CPC (source: EP KR)

**C22C 21/00** (2013.01 - EP); **C22C 21/02** (2013.01 - EP KR); **C22C 21/08** (2013.01 - EP)

Cited by

CN103805817A

Designated contracting state (EPC)

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE

DOCDB simple family (publication)

**EP 1098009 A2 20010509**; **EP 1098009 A3 20010530**; **EP 1098009 B1 20020703**; **EP 1098009 B2 20080924**; AT E220122 T1 20020715; AU 6966400 A 20010510; DE 19953212 A1 20010531; DE 50000260 D1 20020808; ES 2178998 T3 20030116; JP 2001181770 A 20010703; KR 100512154 B1 20050905; KR 20010070185 A 20010725; PT 1098009 E 20021129

DOCDB simple family (application)

**EP 00121632 A 20001004**; AT 00121632 T 20001004; AU 6966400 A 20001101; DE 19953212 A 19991105; DE 50000260 T 20001004; ES 00121632 T 20001004; JP 2000336228 A 20001102; KR 20000065135 A 20001103; PT 00121632 T 20001004