

Title (en)

Ultra-high strength metastable austenitic stainless steel containing Ti and a method of producing the same

Title (de)

Hochfester, metastabiler austenitischer rostfreier Stahl, der auch Titan enthält und Verfahren zu seiner Herstellung

Title (fr)

Acier austénitique inoxydable et métasable à haute résistance mécanique contenant du titane et procédé pour sa fabrication

Publication

**EP 1106706 A1 20010613 (EN)**

Application

**EP 00122438 A 20001013**

Priority

JP 31524899 A 19991105

Abstract (en)

An ultra-high strength metastable austenitic stainless steel exhibiting a tensile strength of not less than 2200 N/mm<sup>2</sup> has a chemical composition comprising, in mass%, not more than 0.15 % of C, more than 1.0 to 6.0 % of Si, not more than 5.0 % of Mn, 4.0-10.0 % of Ni, 12.0-18.0 % of Cr, not more than 3.5 % of Cu, not more than 5.0 % of Mo, not more than 0.02 % of N, 0.1-0.5 % of Ti, optionally one or both of not more than 0.5 % of V and not more than 0.5 % of Nb, and the balance of Fe and unavoidable impurities, satisfies Si + Mo  $\geq$  3.5 %, has a value of Md(N) defined by the equation Md(N) = 580 - 520C - 2Si - 16Mn - 16Cr - 23Ni - 300N - 26Cu - 10Mo of 20-140, exhibits a cold worked multiphase texture composed of 50-95 vol% of martensite phase and the remainder substantially of austenite phase, and has Mo-system precipitates and Ti-system precipitates distributed in the martensite phase.

IPC 1-7

**C22C 38/44**; **C22C 38/58**; **C22C 38/00**; **C21D 8/02**

IPC 8 full level

**C21D 8/02** (2006.01); **C21D 9/46** (2006.01); **C22C 38/00** (2006.01); **C22C 38/34** (2006.01); **C22C 38/42** (2006.01); **C22C 38/44** (2006.01); **C22C 38/46** (2006.01); **C22C 38/48** (2006.01); **C22C 38/50** (2006.01); **C22C 38/58** (2006.01)

CPC (source: EP KR US)

**C21D 8/0205** (2013.01 - EP US); **C22C 38/001** (2013.01 - EP US); **C22C 38/34** (2013.01 - EP US); **C22C 38/42** (2013.01 - EP US); **C22C 38/44** (2013.01 - EP KR US); **C22C 38/46** (2013.01 - EP US); **C22C 38/48** (2013.01 - EP US); **C22C 38/50** (2013.01 - EP US); **C22C 38/58** (2013.01 - EP US); **C21D 8/0226** (2013.01 - EP US); **C21D 8/0236** (2013.01 - EP US); **C21D 8/0247** (2013.01 - EP US); **C21D 2211/001** (2013.01 - EP US); **C21D 2211/008** (2013.01 - EP US)

Citation (search report)

- [X] US 5035855 A 19910730 - UTSUNOMIYA TAKESHI [JP], et al
- [X] US 4878955 A 19891107 - HOSHINO KAZUO [JP], et al
- [X] PATENT ABSTRACTS OF JAPAN vol. 018, no. 251 (C - 1199) 13 May 1994 (1994-05-13)
- [X] PATENT ABSTRACTS OF JAPAN vol. 012, no. 279 (C - 517) 1 August 1988 (1988-08-01)
- [X] PATENT ABSTRACTS OF JAPAN vol. 1995, no. 09 31 October 1995 (1995-10-31)
- [X] PATENT ABSTRACTS OF JAPAN vol. 1999, no. 14 22 December 1999 (1999-12-22)

Cited by

DE102014217369A1; CN104152804A; DE102005030413C5; DE102005030413B3; EP3360981A1; US11788176B2; WO2016034390A1; WO2018146050A1; WO2006068610A1; US8337748B2; US9133538B2; US9873932B2; US8877121B2; US9624564B2; US10323308B2; US8337749B2; US9121089B2; US9643236B2; US9822435B2; US8313691B2; US8858872B2; US9617628B2; US10370748B2

Designated contracting state (EPC)

DE SE

DOCDB simple family (publication)

**EP 1106706 A1 20010613**; **EP 1106706 B1 20030625**; CN 1197986 C 20050420; CN 1295139 A 20010516; DE 60003511 D1 20030731; DE 60003511 T2 20040429; JP 2001131713 A 20010515; KR 100682802 B1 20070215; KR 20010051451 A 20010625; TW 573024 B 20040121; US 6440236 B1 20020827

DOCDB simple family (application)

**EP 00122438 A 20001013**; CN 00133810 A 20001103; DE 60003511 T 20001013; JP 31524899 A 19991105; KR 20000065368 A 20001104; TW 89121166 A 20001011; US 70389600 A 20001102