

Title (en)

METHOD FOR PHOSPHATIZING ZINC OR ALUMINIUM SURFACES

Title (de)

VERFAHREN ZUR PHOSPHATIERUNG VON ZINK- ODER ALUMINIUMOBERFLÄCHEN

Title (fr)

PROCEDE POUR LA PHOSPHATISATION DE SURFACES EN ZINC OU EN ALUMINIUM

Publication

**EP 1155163 B1 20031105 (DE)**

Application

**EP 00905014 A 20000203**

Priority

- DE 19905479 A 19990210
- EP 0000865 W 20000203

Abstract (en)

[origin: WO0047799A1] The invention relates to a method for phosphatizing zinc or aluminium surfaces with a phosphatizing solution containing 0.5 to 2.0 g/l Zn<2+>, 0.3 to 2.0 g/l Ni<2+>, 0.1 to 0.4 g/l NH<sub>2</sub>OH, at least 3.0 g/l NO<sub>3</sub><-> and 10.0 to 20.0 g/l phosphate (calculated as P<sub>2</sub>O<sub>5</sub>). Said solution is applied to the surfaces by immersion or spraying at 35 to 75 DEG C, the immersion time being 0.5 to 10 minutes and the spraying time being 3 seconds to 5 minutes.

IPC 1-7

**C23C 22/18; C23C 22/36; C23C 22/13**

IPC 8 full level

**C23C 22/13** (2006.01); **C23C 22/18** (2006.01); **C23C 22/36** (2006.01)

CPC (source: EP)

**C23C 22/13** (2013.01); **C23C 22/184** (2013.01); **C23C 22/362** (2013.01); **C23C 22/365** (2013.01)

Designated contracting state (EPC)

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE

DOCDB simple family (publication)

**WO 0047799 A1 20000817**; AT E253651 T1 20031115; AU 2669400 A 20000829; CA 2362556 A1 20000817; DE 19905479 A1 20000817;  
DE 50004321 D1 20031211; EP 1155163 A1 20011121; EP 1155163 B1 20031105

DOCDB simple family (application)

**EP 0000865 W 20000203**; AT 00905014 T 20000203; AU 2669400 A 20000203; CA 2362556 A 20000203; DE 19905479 A 19990210;  
DE 50004321 T 20000203; EP 00905014 A 20000203