

Title (en)

CORROSION-FREE IRON-NICKEL ALLOY FOR RESIDUAL-CURRENT CIRCUIT-BREAKERS AND CLOCKWORKS

Title (de)

KORROSIONSFREIE EISEN-NICKEL-LEGIERUNG FÜR FEHLERSTROMSCHUTZSCHALTER UND UHRENLAUFWERKE

Title (fr)

ALLIAGE FER-NICKEL ANTI-CORROSION POUR DISJONCTEURS DE COURANT DE FUITE ET PIECES DE MOUVEMENTS D'HORLOGERIE

Publication

EP 1169487 A1 20020109 (DE)

Application

EP 00926919 A 20000413

Priority

- DE 29906700 U 19990415
- DE 19932473 A 19990712
- EP 0003349 W 20000413

Abstract (en)

[origin: WO0063454A1] An alloy on the basis of 40-55 wt. % nickel and iron becomes corrosion-proof by alloying it with 0.5-6 wt. % chromium. The surfaces of the components produced by said alloy are hardened by nitrating. The alloy is particularly useful for the use in relays and clockworks. The concentration of Ca, Mg and S together amounts to less than 0.009 wt. %.

IPC 1-7

C22C 38/08; **C22C 38/40**; **C22C 19/05**; **H01F 1/147**; **H02K 1/02**; **H02K 37/16**; **C23C 8/24**

IPC 8 full level

C22C 19/05 (2006.01); **C22C 30/00** (2006.01); **C22C 38/08** (2006.01); **C22C 38/40** (2006.01); **H01H 71/32** (2006.01); **H02K 1/02** (2006.01)

CPC (source: EP)

C22C 19/058 (2013.01); **C22C 30/00** (2013.01); **C22C 38/08** (2013.01); **C22C 38/40** (2013.01); **H01H 71/321** (2013.01); **H02K 1/02** (2013.01); **H01H 71/323** (2013.01)

Citation (search report)

See references of WO 0063454A1

Designated contracting state (EPC)

CH DE ES FR LI

DOCDB simple family (publication)

WO 0063454 A1 20001026; EP 1169487 A1 20020109

DOCDB simple family (application)

EP 0003349 W 20000413; EP 00926919 A 20000413