

Title (en)  
Soft roll

Title (de)  
Elastische Walze

Title (fr)  
Rouleau élastique

Publication  
**EP 1188859 A2 20020320 (DE)**

Application  
**EP 01121948 A 20010912**

Priority  
DE 10046055 A 20000918

Abstract (en)

Roller has hard roller core (10) with outer elastic cladding (12). The cladding has elastic matrix material (16) with embedded fibers (19) with diameter of  $\leq 800$  nm, so that outer surface (20) of the cladding is highly polished with Ra value of  $\leq 0.6$  microns. The elastic cladding has thickness of 3-20 mm. The matrix material also has embedded powder bulking materials (17) with outer dimensions of  $\leq 1$  micron at least in one direction. The paper web polishing roller has embedded fibers in the elastic matrix cladding material with a diameter of  $\leq 500$  nm, (preferably  $\leq 200$  nm). The outer dimensions of the embedded powder materials are  $\leq 800$  nm in at least one direction, (preferably  $\leq 200$  nm). The powder materials are in round or spherical particles, at least partially of carbon. The fibers are carbon fibers. The materials for the fibers and the bulking powders have a thermal conductivity which is higher than the matrix material, and they are evenly distributed through the matrix. The polished elastic cladding surface has a roughness value Ra of  $\leq 0.5$  microns, (preferably  $\leq 0.2$  microns, more preferably  $\leq 0.1$  microns). An Independent claim is included for a roller production process, where the elastic cladding is formed with embedded fibers and bulking powders.

Abstract (de)

Es wird eine Walze, insbesondere zum Glätten von Papierbahnen, beschrieben, die einen insbesondere aus Metall bestehenden harten Walzenkern (10) besitzt. Der Walzenkern (10) ist an seiner Außenseite mit einer elastischen Bezugsschicht versehen, die aus einem elastischen Matrixmaterial (16) und in das Matrixmaterial (16) eingebetteten Fasern (19) besteht. Der Durchmesser der Faser (19) ist kleiner als 800 nm, so daß die Oberfläche der elastischen Bezugsschicht (20) eine extrem hohe Glätte, insbesondere einen Ra-Wert von unter ca. 0,6  $\mu\text{m}$  besitzt. Die Dicke der elastischen Bezugsschicht beträgt zwischen 3 und 20 mm. Zusätzlich zu den Fasern (19) sind in dem Matrixmaterial (16) puderförmige Füllstoffe (17) eingebettet, deren äußere Abmessungen zumindest in einer Richtung jeweils kleiner als 1  $\mu\text{m}$  sind. Weiterhin wird ein Verfahren zum Herstellen einer solchen Walze beschrieben. <IMAGE>

IPC 1-7  
**D21G 1/02**

IPC 8 full level  
**D21G 1/02** (2006.01)

CPC (source: EP US)  
**D21G 1/0233** (2013.01 - EP US); **Y10T 29/49551** (2015.01 - EP US); **Y10T 29/49563** (2015.01 - EP US)

Cited by  
EP2644773A1; EP2462280A1

Designated contracting state (EPC)  
AT DE FI SE

DOCDB simple family (publication)  
**EP 1188859 A2 20020320; EP 1188859 A3 20030604; EP 1188859 B1 20060705**; AT E332410 T1 20060715; DE 10046055 A1 20020328;  
DE 50110388 D1 20060817; US 2002045523 A1 20020418; US 6682467 B2 20040127

DOCDB simple family (application)  
**EP 01121948 A 20010912**; AT 01121948 T 20010912; DE 10046055 A 20000918; DE 50110388 T 20010912; US 95319901 A 20010917