

Title (en)
COLORED SPECTROZONAL SILVER-HALIDE PHOTOGRAPHIC MATERIAL

Title (de)
SPEKTRAL SENSIBILISIERTES PHOTOGRAPHISCHES SILBERHALOGENIDFARBMATERIAL

Title (fr)
MATERIAU PHOTOGRAPHIQUE COULEUR A BANDES SPECTRALES A BASE D'HALOGENURES D'ARGENT

Publication
EP 1193547 A1 20020403 (EN)

Application
EP 00925769 A 20000327

Priority
• RU 0000103 W 20000327
• RU 2000102205 A 20000201

Abstract (en)
The invention relates to area of colour photographic materials for registration of a colour image in visible and infra-red area. The material comprises an antihalo backing layer on the one side of a polymer support and at least two light-sensitive layers prepared from silver halide emulsion, including colour forming couplers and sensitizing dyes, auxiliary and protective gelatin layers on the other side of the polymer support, said light-sensitive layers are prepared from silver bromide-iodide emulsion with octahedral or flattened microcrystals with an average size of the grain 0,5-1,5 μm or from their mixture and one light-sensitive layer contains as infra-red sensitizing dye one or more compounds of the formula <CHEM> where A = H, A<1> = OCH₂CH₂CH₂SO₃<->, O - lower alkyl, A and A<2> together = CH₂C-(CH₃)₂CH₂ <->, A<2> = H, lower alkyl, B = H, 5,5'-di-OCH₃, 6,6'-di-SCH₃, R = lower alkyl, (CH₂)₃SO₃<->, n = 0,1; X = CH₃C₆H₄ SO₃<->, J,-CH₃SO₃<->, the alkaline metal or is absent; the second light-sensitive layer contains as orthochromatic sensitizing dye more than one compounds of the formula <CHEM> where Y = O, N, A = lower alkyl or is absent, A<1> = H, lower alkyl, B = 5,5'-COOC₂H₅, 5,5'-C₆H₅, R, R' = lower alkyl, (CH₂)₃SO₃<->, ÄKÜ <+> = NHC₅H₅ or is absent and /or the third light-sensitive layer contains as panchromatic sensitizing of dye one or more compounds of the formula <CHEM> where A= lower alkyl, B = 4,5-benzo, 4,5-thieno, B<1> = 5-OCH₃, 5-C₆H₅, 4',5'-benzo, 5-Cl, 5-CH₃; R, R<1> = lower alkyl, (CH₂)₃SO₃<->, ÄKÜ <+> = HN (C₂H₅)₃, HN(C₄H₉)₃, C₅H₅-NH, the alkaline metal, 3,3'-diethylthiazolynecarbocyanine, or is absent, and between light-sensitive layers auxiliary gelatin layers including hardener are coated. In addition the light-sensitive layers can contain activators of spectral sensitization. The auxiliary gelatin layers can include derivatives of triazine-1,3,5 as a hardener. It is desirable to add into light-sensitive layers a mixture of silver bromide-iodide photographic emulsions with octahedral microcrystals and with flattened microcrystals in the ratio 1:9-9:1. The material according to the invention has a high resolving power (R = 110-160 mm<-1>), i.e. in 1,6-2,3 times higher, than prototype, and more high light sensitivity.

IPC 1-7
G03C 7/20; **G03C 1/26**

IPC 8 full level
G03C 1/12 (2006.01); **G03C 1/20** (2006.01); **G03C 7/30** (2006.01); **G03C 1/18** (2006.01)

CPC (source: EP)
G03C 1/127 (2013.01); **G03C 1/20** (2013.01); **G03C 7/3029** (2013.01); **G03C 7/3041** (2013.01); **G03C 1/18** (2013.01); **G03C 2007/3015** (2013.01)

Cited by
AU2013243378B2

Designated contracting state (EPC)
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE

DOCDB simple family (publication)
WO 0157593 A1 20010809; **WO 0157593 A8 20011206**; **WO 0157593 A9 20020103**; EP 1193547 A1 20020403; EP 1193547 A4 20030709; RU 2172512 C1 20010820

DOCDB simple family (application)
RU 0000103 W 20000327; EP 00925769 A 20000327; RU 2000102205 A 20000201