

Title (en)
Curtain coating device

Title (de)
Vorhang-Auftragsvorrichtung

Title (fr)
Dispositif de revêtement par rideau

Publication
EP 1208917 A2 20020529 (DE)

Application
EP 01124923 A 20011019

Priority
DE 10057729 A 20001122

Abstract (en)

[origin: DE10057729A1] The coating station to apply at least two coating layers to a moving paper or cardboard web substrate (U), using a liquid or paste coating medium, has two applicators (16,22) with jets (16a,22a) to give coating curtains (28,30) which fall on to the surface (14a) of the moving web (14). The gap (D) between the application points, where the coating curtains strike the web, is 100-500 mm. The web coating applicator, using two coating curtains, applies the first layer (20) with a coating medium (18) with a lower water retention than the coating medium (24) for the second layer (26). The coating for the first layer has a density at least 10% higher than the coating for the second layer, and the first coating has a higher viscosity than the second coating. The coatings are of a watery solution or dispersion with solid particles of mineral pigments or microscopic plastics particles e.g. plastics pigments or ink-filled micro-capsules, or starch. The coatings have a solid content of 5-70 wt.%. The viscosity of the coatings, by Brookfield at 100 rpm, is 10-2000 mPas. The first coating is a barrier layer, e.g. of a starch solution with a solid content of 2-30 wt.% with a viscosity by Brookfield at 100 rpm of 10-150 mPas, and a density of 0.8-1.1 g/cm³. The medium is applied to give the first layer a thickness of 2-20 ml/m² on the substrate. The second coating layer is a dispersion of micro-capsules, filled with ink, with a capsule diameter of 5-12 µm. The second coating medium has a solid content of 20-50 wt.% and a viscosity, by Brookfield at 100 rpm, of 100-400 mPas. The second coating medium is applied with a layer thickness of 5-30 ml/m² on the substrate. At least one of the coating media is applied in ready dosages on to the moving substrate. A unit (42) to generate an underpressure is in the zone (44) between the applicators. At least one guide (32,34,36) is in the falling paths of the coating curtains, to direct the curtains over their whole width for at least a part of their falling path. The coatings fall in a curtain over a height of 40-400 mm. The coatings are applied to the substrate at a rate of 4-100 l/min. for each meter of web width. The web movement speed is up to 3000 m/min. for graphic papers, and at least 200 m/min. for cardboard. Graphic papers for coating have a paper weight of 30-150 g/m², and cardboard for coating has a weight of 150-1000 g/m².

Abstract (de)

Die Erfindung betrifft eine Vorrichtung (10) zum Auftragen wenigstens einer ersten Schicht (20) und wenigstens einer zweiten Schicht (26) flüssigen oder pastösen Auftragsmediums (18, 24), insbesondere wässriger Pigmentsuspension, auf einen laufenden Untergrund (U), wobei der Untergrund (U) bei direktem Auftrag die Oberfläche (14a) einer Materialbahn (14), insbesondere aus Papier oder Karton, ist. Die Vorrichtung (10) umfasst wenigstens zwei Vorhang-Auftragswerke (16, 22), von denen jedes das jeweilige Auftragsmedium (18, 24) aus einer Abgabedüse (16a, 22a) als sich im Wesentlichen schwerkraftbedingt bewegenden Vorhang oder Schleier (28, 30) an den Untergrund (U) abgibt. Die beiden Auftragsmedium-Vorhänge (28, 30) treffen dabei in einem Abstand (D) von zwischen etwa 100 mm und etwa 500 mm auf dem Untergrund (U) auf. <IMAGE>

IPC 1-7
B05C 5/00

IPC 8 full level
B05D 1/30 (2006.01); **B05C 5/00** (2006.01); **B05C 9/06** (2006.01)

CPC (source: EP US)
B05C 5/005 (2013.01 - EP US); **B05C 5/008** (2013.01 - EP US); **B05C 9/06** (2013.01 - EP US)

Citation (applicant)
• DE 19716647 A1 19981022 - JAGENBERG PAPIERTECH GMBH [DE]
• DE 19513531 A1 19961017 - DU PONT DEUTSCHLAND [DE]

Cited by
EP2082811A3; EP2082811A2; WO2013171776A3; US11407001B2; WO2018137932A1

Designated contracting state (EPC)
AT DE FI SE

DOCDB simple family (publication)
EP 1208917 A2 20020529; **EP 1208917 A3 20050330**; **EP 1208917 B1 20080227**; AT E387262 T1 20080315; DE 10057729 A1 20020523; DE 20023956 U1 20071206; DE 50113656 D1 20080410; JP 2002192047 A 20020710; JP 3942874 B2 20070711; US 2002066404 A1 20020606; US 2004166244 A1 20040826

DOCDB simple family (application)
EP 01124923 A 20011019; AT 01124923 T 20011019; DE 10057729 A 20001122; DE 20023956 U 20001122; DE 50113656 T 20011019; JP 2001353349 A 20011119; US 78386404 A 20040223; US 99630401 A 20011121