

Title (en)

Flameproof fleece containing regenerated cellulose fibres

Title (de)

Flammfestes Vlies, das Celluloseregeneratfasern umfasst

Title (fr)

Nappe ininflammable contenant des fibres cellulosiques régénérées

Publication

EP 1229165 A1 20020807 (DE)

Application

EP 02000887 A 20020115

Priority

DE 10104277 A 20010131

Abstract (en)

Cellulose fleece has a fire-retardant additive with a limiting oxygen index (LOI) of at least 65. The cellulose material is Lycocell which may be crushed and converted to fibre. The fire retardant fleece has a specific weight of 11 to 150 g/m. The fire retardant additive is cyclic and acyclic phosphonate and di-phosphonate-ester, alkyl-phosphonic acids, chlorinated phosphoric compounds, organic phosphor nitric oxide compounds, or inorganic phosphor compounds, pyro-phosphoric acids, organic nitric oxide compounds, or any desired combination of these. The fleece incorporates at least 40 per cent by weight fire-retardant additives. Also claimed is a process to manufacture the fire-retardant fleece using a paper manufacturing machine and primary fibre material having a crushability of 5 to 75 SR. The flame retardant agent is applied by spray beams in a glue press.

Abstract (de)

Beschrieben wird flammfestes Vlies (9), das Celluloseregeneratfasern umfasst, die mit einem Flammschutzmittel beaufschlagt sind, wobei das flammfeste Vlies einen LOI-Wert (limiting oxygen index) von mindestens 65 aufweist, sowie ein Verfahren zur Herstellung desselben auf einer Papiermaschine.

IPC 1-7

D21H 21/34; D21H 23/24

IPC 8 full level

D21H 21/34 (2006.01); **D21H 13/08** (2006.01); **D21H 17/07** (2006.01); **D21H 17/10** (2006.01); **D21H 17/63** (2006.01)

CPC (source: EP)

D21H 21/34 (2013.01); **D21H 13/08** (2013.01); **D21H 17/07** (2013.01); **D21H 17/10** (2013.01); **D21H 17/63** (2013.01)

Citation (search report)

- [YA] DE 2045118 A1 19710624
- [A] US 3819518 A 19740625 - ENDLER A
- [A] GB 2325248 A 19981118 - CROMPTON J R PLC [GB]
- [Y] DATABASE PAPERCHEM [online] THE INSTITUTE OF PAPER SCIENCE AND TECHNOLOGY, ATLANTA, GA, US; MIYAMOTO, H. ET AL: "PAPER SUBSTITUTES", XP002192549, retrieved from DIALOG & JP S4994903 A 19740909
- [YA] POPESCU F N ET AL: "PHOSPHORIC ACID-UREA POLYCONDENSATE FIREPROOFING AGENT FOR PAPER SUBSTITUTES", ABSTRACT BULLETIN OF THE INSTITUTE OF PAPER CHEMISTRY, THE INSTITUTE OF PAPER CHEMISTRY-LIBRARY. APPLETON, US, vol. 59, no. 6, 1 December 1988 (1988-12-01), pages 719, XP000031610
- [Y] DATABASE WPI Section Ch Week 197544, Derwent World Patents Index; Class A17, AN 1975-73155W, XP002192551
- [YA] DATABASE PAPERCHEM [online] THE INSTITUTE OF PAPER SCIENCE AND TECHNOLOGY, ATLANTA, GA, US; MOSIO-MOSIEWSKI, J: "Decreasing the Combustibility of Paper", XP002192550, retrieved from DIALOG & PRZEM. CHEM. 64, NO. 8: 381-383 (1985). [POL.]
- [YA] DATABASE WPI Section Ch Week 197639, Derwent World Patents Index; Class A11, AN 1976-73097X, XP002192552

Cited by

DE102004015356A1; US7491294B2; US7622517B2; WO2005038133A1

Designated contracting state (EPC)

DE ES FR GB

DOCDB simple family (publication)

EP 1229165 A1 20020807; EP 1229165 B1 20060329; DE 10104277 A1 20020814; DE 10104277 B4 20080221; DE 50206179 D1 20060518; ES 2177481 T1 20021216; ES 2177481 T3 20060916

DOCDB simple family (application)

EP 02000887 A 20020115; DE 10104277 A 20010131; DE 50206179 T 20020115; ES 02000887 T 20020115