

Title (en)

Cell separator made of a thermoplastic resin porous film

Title (de)

Zellseparator aus einem porösen Film aus thermoplastischem Harz

Title (fr)

Séparateur de pile constitué d'un film poreux constitué d'une résine thermoplastique

Publication

EP 1249269 A2 20021016 (EN)

Application

EP 02008134 A 20020411

Priority

JP 2001113832 A 20010412

Abstract (en)

Disclosed is a porous film made of thermoplastic resin having micropores, wherein the micropores are formed from a 3-dimensional network made of trunk fibrils extending in one direction of the film and branch fibrils through which the trunk fibrils are connected to one another, and the density of the branch fibrils formed is higher than the density of the trunk fibrils formed, and the average pore diameter d (μm) of the micropores as determined by a bubble-point method (ASTM F316-86) and the average pore radius r (μm) of the micropores as determined by mercury porosimetry (JIS K1150) satisfy the relationship $1.20 \leq 2r/d \leq 1.70$. The porous film has practically sufficient mechanical strength and excellent in ion permeability.

A porous thermoplastic resin film (15) has micropores formed from a three-dimensional network made of trunk fibrils extending in one direction, and branch fibrils through which trunk fibrils are connected to one another. Density of branch fibrils is higher than that of trunk fibrils. Average pore diameter and radius of micropores satisfy a predetermined relation. A porous thermoplastic resin film has micropores formed from a three-dimensional network made of trunk fibrils extending in one direction, and branch fibrils through which trunk fibrils are connected to one another. The density of branch fibrils is higher than that of trunk fibrils. Average pore diameter (d) (in Microm) of micropores determined by bubble-point method ASTM F316-86 and radius (r) (in Microm) of micropores determined by mercury porosimetry JIS K1150 satisfy the relationship $1.2 = 2r/d = 1.7$.

IPC 1-7

B01D 67/00; **C08J 9/00**; **H01M 2/16**; **C08J 5/18**

IPC 8 full level

B01D 67/00 (2006.01); **C08J 9/00** (2006.01); **B01D 69/02** (2006.01); **B01D 69/14** (2006.01); **B01D 71/26** (2006.01); **B29C 55/00** (2006.01); **C08J 5/18** (2006.01); **H01G 9/02** (2006.01); **H01M 10/052** (2010.01); **H01M 50/417** (2021.01); **B29K 91/00** (2006.01); **B29K 105/04** (2006.01); **B29K 105/16** (2006.01); **H01M 50/489** (2021.01); **H01M 50/497** (2021.01)

CPC (source: EP KR US)

B01D 67/0027 (2013.01 - EP US); **B01D 67/009** (2013.01 - EP US); **B01D 69/02** (2013.01 - EP KR US); **B01D 71/261** (2022.08 - EP KR US); **B29C 55/005** (2013.01 - EP US); **C08J 5/18** (2013.01 - EP KR US); **C08J 5/2231** (2013.01 - KR); **C08J 9/22** (2013.01 - KR); **H01G 9/02** (2013.01 - EP KR US); **H01M 10/052** (2013.01 - EP KR US); **H01M 50/417** (2021.01 - EP KR US); **H01M 50/44** (2021.01 - EP KR US); **H01M 50/489** (2021.01 - KR); **B01D 2323/12** (2013.01 - EP KR US); **B29K 2023/0683** (2013.01 - EP KR US); **B29K 2091/00** (2013.01 - EP KR US); **B29K 2105/04** (2013.01 - EP KR US); **B29K 2105/16** (2013.01 - EP KR US); **H01M 50/489** (2021.01 - EP US); **H01M 50/497** (2021.01 - EP US); **Y02E 60/10** (2013.01 - EP KR); **Y10T 428/249978** (2015.04 - EP US); **Y10T 428/249979** (2015.04 - EP US)

Cited by

EP1201295A3

Designated contracting state (EPC)

DE FR GB IT NL

DOCDB simple family (publication)

EP 1249269 A2 20021016; **EP 1249269 A3 20070815**; **EP 1249269 B1 20130605**; CA 2381509 A1 20021012; CN 1235953 C 20060111; CN 1381515 A 20021127; JP 2002309024 A 20021023; JP 4880824 B2 20120222; KR 100995267 B1 20101119; KR 20020079581 A 20021019; KR 20090036090 A 20090413; TW I280255 B 20070501; US 2002192454 A1 20021219

DOCDB simple family (application)

EP 02008134 A 20020411; CA 2381509 A 20020411; CN 02105529 A 20020412; JP 2001113832 A 20010412; KR 20020019709 A 20020411; KR 20090016430 A 20090226; TW 91106729 A 20020403; US 11425402 A 20020403