

Title (en)
PROCESS FOR MANUFACTURE OF ZEOLITES AND ZEOLITE MIXTURES HAVING ENHANCED CATION EXCHANGE PROPERTIES,
PRODUCTS PRODUCED THEREBY, AND DETERGENT COMPOSITIONS FORMULATED THEREWITH

Title (de)
VERFAHREN ZUR HERSTELLUNG VON ZEOLITEN UND ZEOLITENMISCHUNGEN MIT VERBESSERTEN
KATIONENAUSTAUSCHEIGENSCHAFT SOWIE DADURCH HERGESTELLTE PRODUKTE UND WASCHMITTELZUSAMMENSETZUNGEN

Title (fr)
PROCEDE POUR LA FABRICATION DE ZEOLITES ET MELANGES DE ZEOLITES AYANT DES PROPRIETES D'ECHANGE CATIONIQUE
AUGMENTEES, DES PRODUITS AINSI OBTENUS, ET COMPOSITIONS DE DETERGENT FORMULEES AVEC CEUX-CI

Publication
EP 1265814 A2 20021218 (EN)

Application
EP 01916640 A 20010315

Priority

- US 0108107 W 20010315
- US 19018500 P 20000317
- US 21307600 P 20000621
- US 24663200 P 20001108

Abstract (en)
[origin: WO0170629A2] A zeolite A or an A/X mixture having an LCC > 70g liquid/100g zeolite (hydrated) and a cold water CER > 200 mg CaCO₃/gram anhydrous zeolite (hydrated). The zeolite product may have a crystal size of 0.1-0.7 microns, a bulk density of 0.19-0.37 g/ml, and a median particle size of 1-5 microns. A process for making zeolite A or A/X mixtures is also claimed, including mixing a sodium silicate solution, a sodium aluminate solution, and an amorphous aluminosilicate initiator gel in a mixing vessel to create an aluminosilicate synthesis gel, and crystallizing the aluminosilicate synthesis gel to form zeolite crystals. The sodium aluminate solution may be added gradually to at least the sodium silicate solution at a rate of about 1-5% of the total batch alumina per minute, and/or a percentage of the total batch alumina may be added as alumina trihydrate (ATH) powder. The amount of total batch alumina added as an undissolved source of soluble alumina and the presence or absence of initiator or "seed" gel determines whether the resulting zeolite product is an A/X mixture or only zeolite A. A process to augment the yield of a synthesis mixture is also claimed, comprising providing undissolved alumina in substantial excess of stoichiometric requirements in a primary crystallization step, yielding a slurry of crystalline zeolite. A in an alumina-enriched mother liquor, and then adding soluble silicate to initiate a second stage of very rapid crystallization. Detergents containing zeolites of this invention are claimed.

IPC 1-7
C01B 39/14

IPC 8 full level
C01B 39/02 (2006.01); **C01B 39/14** (2006.01); **C01B 39/22** (2006.01); **C11D 3/12** (2006.01); **C11D 3/386** (2006.01); **C11D 3/395** (2006.01); **C11D 3/42** (2006.01); **C11D 3/48** (2006.01); **C11D 3/50** (2006.01)

CPC (source: EP KR US)
C01B 39/023 (2013.01 - EP US); **C01B 39/14** (2013.01 - EP US); **C01B 39/16** (2013.01 - KR); **C11D 3/128** (2013.01 - EP US); **Y10S 423/21** (2013.01 - EP US); **Y10S 423/24** (2013.01 - EP US)

Citation (search report)
See references of WO 0170629A2

Cited by
CN109790040A; CN102992342A

Designated contracting state (EPC)
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR

DOCDB simple family (publication)
WO 0170629 A2 20010927; WO 0170629 A3 20011206; WO 0170629 B1 20020207; AT E266603 T1 20040515; AU 4363801 A 20011003; BR 0109300 A 20021224; CA 2402679 A1 20010927; CA 2402679 C 20071204; CN 1223400 C 20051019; CN 1420845 A 20030528; DE 60103260 D1 20040617; DE 60103260 T2 20050519; EP 1265814 A2 20021218; EP 1265814 B1 20040512; ES 2221891 T3 20050116; HK 1051993 A1 20030829; JP 2003528022 A 20030924; JP 4023779 B2 20071219; KR 100488611 B1 20050511; KR 20030008218 A 20030124; US 2001053741 A1 20011220; US 2003050219 A1 20030313; US 6641796 B2 20031104

DOCDB simple family (application)
US 0108107 W 20010315; AT 01916640 T 20010315; AU 4363801 A 20010315; BR 0109300 A 20010315; CA 2402679 A 20010315; CN 01807508 A 20010315; DE 60103260 T 20010315; EP 01916640 A 20010315; ES 01916640 T 20010315; HK 03104322 A 20030617; JP 2001568845 A 20010315; KR 20027012272 A 20010315; US 22841702 A 20020827; US 81091401 A 20010316