

Title (en)
Flux-contained welding wire

Title (de)
Flussmittelkerndraht zum Schweißen

Title (fr)
Fil à âme de flux pour le soudage

Publication
EP 1277538 A1 20030122 (EN)

Application
EP 02255053 A 20020718

Priority
JP 2001220200 A 20010719

Abstract (en)
A flux-contained welding wire is provided wherein a conductive core wire (4) can be disposed without any complicate manufacturing steps performed on a metal outer layer (2). Flux (3) is filled inside of the metal outer layer (2). The conductive core wire (4) is disposed nearly in the center of the flux (3) without being supported by the metal outer layer (2). The flux contains 20-80 weight% of metal powder. A weight% of the weight of the flux to the weight of the welding wire per unit length is set in a range of 6.5-30 weight%. The weight% of the weight of the conductive core wire to the weight of the welding wire per unit length is set in a range of 1.5-15 weight%.

IPC 1-7
B23K 35/02; **B23K 35/30**

IPC 8 full level
B23K 35/02 (2006.01); **B23K 35/04** (2006.01); **B23K 35/30** (2006.01)

CPC (source: EP US)
B23K 35/0266 (2013.01 - EP US); **B23K 35/3033** (2013.01 - EP US); **B23K 35/0272** (2013.01 - EP US)

Citation (search report)

- [Y] BE 675192 A
- [Y] DE 19523400 A1 19970102 - CASTOLIN SA [CH]
- [A] EP 0015746 A1 19800917 - BEKAERT SA NV [BE]
- [A] US 3834002 A 19740910 - SISSONS A, et al
- [A] GB 1383304 A 19740212 - BRITISH OXYGEN CO LTD
- [A] FR 2177134 A5 19731102 - BRITISH INSULATED CALLENDERS [GB]
- [A] FR 2158621 A5 19730615 - SOUDURE AUTOGENE FRANCAISE

Cited by
CN102873464A; CN102284804A; CN102267017A; EP2666580A1; CN103418929A

Designated contracting state (EPC)
DE GB IT NL SE

DOCDB simple family (publication)
EP 1277538 A1 20030122; **EP 1277538 B1 20080116**; DE 60224616 D1 20080306; DE 60224616 T2 20090115; US 2003052113 A1 20030320; US 6710301 B2 20040323

DOCDB simple family (application)
EP 02255053 A 20020718; DE 60224616 T 20020718; US 19681502 A 20020717