

Title (en)
METHOD FOR MANUFACTURING PRODUCTS

Title (de)
VERFAHREN ZUR HERSTELLUNG VON ERZEUGNISSEN

Title (fr)
PROCEDE POUR LA FABRICATION DE PRODUITS

Publication
EP 1292725 A1 20030319 (DE)

Application
EP 01984036 A 20010122

Priority
• AT 0100015 W 20010122
• RU 2000115910 A 20000621

Abstract (en)
[origin: WO0198562A1] The invention relates to a method for coating products e.g. workpieces (in particular consisting of valve metals or their alloys) by micro arc oxidation or electrophoresis in the presence of at least one additive that is incorporated into an alkaline solution. Said method is characterised in that a nozzle element is placed at a distance of 5-15 mm from the region of the surface of the workpiece to be treated, prior to the application of the coating. The cross-section of the nozzle is selected depending on the geometry of the workpiece to be treated. In addition, by supplying the alkaline solution through the nozzle element, an electric cathode-anode circuit is closed by the uninterrupted stream of solution that is guided in a specifically targeted manner and/or flows freely, to prevent a further cooling of the workpiece and to ensure the fusion of the coating over its entire depth. The additives used consist of powdered components or ultra-disperse powder that is necessary for the chemical composition.
[origin: WO0198562A1] The invention relates to a method for coating products e.g. workpieces (in particular consisting of valve metals or their alloys) by micro arc oxidation or electrophoresis in the presence of at least one additive that is incorporated into an alkaline solution. Said method is characterised in that a nozzle element is placed at a distance of 5-15 mm from the region of the surface of the workpiece to be treated, prior to the application of the coating. The cross-section of the nozzle is selected depending on the geometry of the workpiece to be treated. In addition, by supplying the alkaline solution through the nozzle element, an electric cathode-anode circuit is closed by the uninterrupted stream of solution that is guided in a specifically targeted manner and/or flows freely, to prevent a further cooling of the workpiece and to ensure the fusion of the coating over its entire depth. The additives used consist of powdered components or ultra-disperse powder that is necessary for the chemical composition.

IPC 1-7
C25D 11/04; **C25D 11/26**; **C25D 13/22**

IPC 8 full level
B44C 5/00 (2006.01); **B44C 1/04** (2006.01); **C25D 11/04** (2006.01); **C25D 11/26** (2006.01); **C25D 13/22** (2006.01)

CPC (source: EP US)
C25D 11/04 (2013.01 - EP US); **C25D 11/26** (2013.01 - EP US); **C25D 13/22** (2013.01 - EP US)

Citation (search report)
See references of WO 0198562A1

Designated contracting state (EPC)
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE TR

Designated extension state (EPC)
MK SI

DOCDB simple family (publication)
WO 0198562 A1 20011227; AT E356232 T1 20070315; AU 2817201 A 20020102; CA 2411825 A1 20011227; DE 50112162 D1 20070419; EP 1292725 A1 20030319; EP 1292725 B1 20070307; HU P0301662 A2 20030828; RU 2166434 C1 20010510; SK 18202002 A3 20030911; US 2004026247 A1 20040212

DOCDB simple family (application)
AT 0100015 W 20010122; AT 01984036 T 20010122; AU 2817201 A 20010122; CA 2411825 A 20010122; DE 50112162 T 20010122; EP 01984036 A 20010122; HU P0301662 A 20010122; RU 2000115910 A 20000621; SK 18202002 A 20010122; US 31180903 A 20030707