

Title (en)
MELT-BLOWN NONWOVEN FABRIC

Title (de)
SCHMELZGEBLASENER VLIESTOFF

Title (fr)
NON-TISSE DE FUSION-SOUFFLAGE

Publication
EP 1349973 A2 20031008 (EN)

Application
EP 01272295 A 20011221

Priority
• JP 0111297 W 20011221
• JP 2000390634 A 20001222

Abstract (en)
[origin: WO02052084A2] A melt-blown nonwoven fabric of the present invention is formed from an ethylene-(meth)acrylic acid copolymer having a melt flow rate of 50 to 1000 g/10 min measured at 2.16 kg load and at a temperature of 190 degrees in accordance with ASTM D1238, and a content of acrylic acid or methacrylic acid unit of 2 to 25 weight %. The nonwoven fabric has the sum of values of (tensile strength (g/5 cm))/(basis weight (g/m2)) in machine direction and cross direction of 30 to 100, and a residual strain after 50% extension of no more than 20%, and is excellent in gas permeability, elasticity and moreover moderate strength. The nonwoven fabric is suitable for elasticized fabric components, packaging materials, laminates, etc.

IPC 1-7
D04H 1/56

IPC 8 full level
D01F 6/30 (2006.01); **D01F 6/46** (2006.01); **D04H 1/56** (2006.01); **D04H 13/00** (2006.01)

CPC (source: EP KR)
D01F 6/30 (2013.01 - EP); **D01F 6/46** (2013.01 - EP); **D04H 1/4291** (2013.01 - EP); **D04H 1/56** (2013.01 - EP); **D04H 3/007** (2013.01 - EP); **D04H 3/016** (2013.01 - EP); **D04H 3/16** (2013.01 - EP KR)

Citation (search report)
See references of WO 02052084A2

Designated contracting state (EPC)
DE FR GB

DOCDB simple family (publication)
WO 02052084 A2 20020704; **WO 02052084 A3 20030220**; AU 2002216405 A1 20020708; CN 1483096 A 20040317; EP 1349973 A2 20031008; KR 20030066736 A 20030809

DOCDB simple family (application)
JP 0111297 W 20011221; AU 2002216405 A 20011221; CN 01821121 A 20011221; EP 01272295 A 20011221; KR 20037008370 A 20030620