

Title (en)

High-tensile strength hot-rolled steel sheet excellent in elongation properties and stretch flangeability, and producing method thereof

Title (de)

Zugfestes warmgewalztes Stahlblech mit ausgezeichneter Bruchdehnung und Streckbördelverformfähigkeit und dessen Herstellungsverfahren

Title (fr)

Tôle d'acier laminée à chaud résistant à la traction, ayant une allongement et une déformabilité de bordage par étirage excellente et son procédé de fabrication

Publication

EP 1350859 B1 20041229 (EN)

Application

EP 03006195 A 20030319

Priority

- JP 2002081451 A 20020322
- JP 2003039099 A 20030218

Abstract (en)

[origin: EP1350859A1] A high-tensile strength hot-rolled steel sheet that satisfies, in addition to TS of 780 MPa or more or furthermore 980 MPa or more, TS X EL \geq 20000 MPa% and TS x lambda \geq 82000 MPa%, and a method of producing the same are provided. Specific resolution means are as follows. That is, a high-tensile strength hot-rolled steel sheet including a composition that includes C of 0.04% by mass or more and 0.25% by mass or less; Si of 0.4% by mass or more and 2.0% by mass or less; Mn of 3.0% by mass or less; Al of 0.2% by mass or less; S of 0.007% by mass or less; Ti of 0.08% by mass or more and 0.3% by mass or less; and the balance of Fe and inevitable impurities, in the above, the contents of the C, the Si and the Ti satisfying $(\text{\AA}\% \text{C}\ddot{U}/12 - \text{\AA}\% \text{Ti}\ddot{U}/48)/(\text{\AA}\% \text{Si}\ddot{U}/28) \leq 0.4$; and a microstructure that includes ferrite; bainite; and retained austenite; in the above a fraction of the ferrite in an entire microstructure is 40% or more and an average grain size of the ferrite is 5 μm or less; a fraction of the bainite is in the range of 20% to 48% with respect to an entire microstructure; and a fraction of the retained austenite is in the range of 2% to 7% with respect to an entire microstructure is produced.

IPC 1-7

C22C 38/14; **C22C 38/58**; **C21D 8/02**; **C21D 8/04**

IPC 8 full level

B21B 1/22 (2006.01); **B21B 3/00** (2006.01); **C21D 8/02** (2006.01); **C21D 9/46** (2006.01); **C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/14** (2006.01)

CPC (source: EP KR)

C21D 8/0226 (2013.01 - EP); **C21D 8/0263** (2013.01 - EP); **C22C 38/00** (2013.01 - KR); **C22C 38/02** (2013.01 - EP); **C22C 38/04** (2013.01 - EP); **C22C 38/14** (2013.01 - EP); **C21D 2211/001** (2013.01 - EP); **C21D 2211/002** (2013.01 - EP); **C21D 2211/005** (2013.01 - EP)

Cited by

US11401571B2; EP3260566A4; EP3561101A4; EP3495530A4; EP3395974A4; EP1790737A1; EP3495529A4; DE102017130237A1; EP3495527A4; US7731808B2; US7879164B2; KR100979854B1; EP3495528A4; US2017349967A1; EP3260565A4; US11230755B2; US11085107B2; US11649531B2; US10913988B2; US10689724B2; US8815025B2; US10889879B2; US10752972B2; US8128762B2; US7927433B2; US8257517B2; US11236412B2; US10689737B2; WO2023089012A1

Designated contracting state (EPC)

DE FR

DOCDB simple family (publication)

EP 1350859 A1 20031008; **EP 1350859 B1 20041229**; CN 1296507 C 20070124; CN 1450191 A 20031022; DE 60300242 D1 20050203; DE 60300242 T2 20050602; JP 2004002969 A 20040108; JP 4062118 B2 20080319; KR 100778264 B1 20071122; KR 20030076430 A 20030926

DOCDB simple family (application)

EP 03006195 A 20030319; CN 03107449 A 20030321; DE 60300242 T 20030319; JP 2003039099 A 20030218; KR 20030017697 A 20030321