

Title (en)  
THIN STEEL SHEET FOR AUTOMOBILE EXCELLENT IN NOTCH FATIGUE STRENGTH AND METHOD FOR PRODUCTION THEREOF

Title (de)  
DÜNNES STAHLBLECH FÜR AUTOS MIT HERVORRAGENDER KERBDAUERFESTIGKEIT UND VERFAHREN ZU SEINER HERSTELLUNG

Title (fr)  
FEUILLE MINCE D'ACIER A RESISTANCE DE FATIGUE D'ENTAILLE EXCELLENTE, DESTINEE A UNE AUTOMOBILE, ET PROCEDE DE PRODUCTION

Publication  
**EP 1362930 A4 20041124 (EN)**

Application  
**EP 02700640 A 20020220**

Priority  
• JP 0201498 W 20020220  
• JP 2001049012 A 20010223  
• JP 2001247306 A 20010816

Abstract (en)  
[origin: EP1362930A1] The present invention provides a thin steel sheet, for automobile use, excellent in notch-fatigue strength, and a method for producing said steel sheet. Specifically, the present invention is a thin steel sheet for automobile use excellent in notch-fatigue strength, said steel sheet containing, in mass, 0.01 to 0.3% C, 0.01 to 2% Si, 0.05 to 3% Mn, 0.1% or less P, 0.01% or less S and 0.005 to 1% Al, with the balance consisting of Fe and unavoidable impurities, characterized in that, on a plane at an arbitrary depth within 0.5 mm from the surface of said steel sheet in the thickness direction thereof, the average of the ratios of the X-ray diffraction strength in the orientation component group of  $\bar{1}00\bar{0}<011>$  to  $\bar{2}23\bar{0}<110>$  to random X-ray diffraction strength is 2 or more and the average of the ratios of the X-ray diffraction strength in the three orientation components of  $\bar{5}54\bar{0}<225>$ ,  $\bar{1}11\bar{0}<112>$  and  $\bar{1}11\bar{0}<110>$  to random X-ray diffraction strength is 4 or less and that the thickness of said steel sheet is in the range from 0.5 to 12 mm, and a method for producing said steel sheet by subjecting a steel slab containing aforementioned chemical components to rolling at a total reduction ratio of 25% or more in a temperature range of the Ar3 transformation temperature + 100 DEG C or lower.

<IMAGE>

IPC 1-7  
**C22C 38/00**; **C22C 38/02**; **C22C 38/04**; **C22C 38/06**; **C21D 8/02**; **C21D 9/46**

IPC 8 full level  
**B21B 1/26** (2006.01); **C21D 8/02** (2006.01); **C21D 9/46** (2006.01); **C22C 38/00** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01); **C22C 38/58** (2006.01); **C23C 2/02** (2006.01); **C23C 2/40** (2006.01)

CPC (source: EP KR US)  
**C21D 8/02** (2013.01 - KR); **C21D 8/0226** (2013.01 - EP US); **C21D 8/0273** (2013.01 - EP US); **C22C 38/002** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US); **C23C 2/02** (2013.01 - EP KR US); **C23C 2/0224** (2022.08 - EP KR US); **C23C 2/024** (2022.08 - EP KR US); **C23C 2/40** (2013.01 - EP US)

Citation (search report)  
• [X] EP 1026278 A1 20000809 - NIPPON STEEL CORP [JP]  
• [X] EP 0969112 A1 20000105 - NIPPON STEEL CORP [JP]  
• [X] US 5470529 A 19951128 - NOMURA SHIGEKI [JP], et al  
• [X] WO 9739152 A1 19971023 - CENTRE RECH METALLURGIQUE [BE], et al  
• [E] EP 1201780 A1 20020502 - NIPPON STEEL CORP [JP]  
• [A] EP 0586704 A1 19940316 - NIPPON STEEL CORP [JP]  
• [A] US 4572748 A 19860225 - SUGA MASATAKA [JP], et al  
• [A] EP 0719868 A1 19960703 - KAWASAKI STEEL CO [JP]  
• See references of WO 02066697A1

Cited by  
EP3162908A4; DE102006051545A1; EP2730672A4; EP2698442A4; EP1806421A4; EP1808505A4; EP2700730A3; EP2692895A4; CN101974722A; EP2599887A4; US9587319B2; WO2008082134A1; US9347122B2; US10060006B2; US9546413B2; US9670569B2; US8057913B2; US8802241B2; US9523139B2; US9567658B2; US9631265B2; US10167539B2; US10226800B2; US10266928B2; EP1444374B1

Designated contracting state (EPC)  
DE FR

DOCDB simple family (publication)  
**EP 1362930 A1 20031119**; **EP 1362930 A4 20041124**; CA 2438393 A1 20020829; CN 1221680 C 20051005; CN 1492938 A 20040428; JP 2002322533 A 20021108; JP 3927384 B2 20070606; KR 100572762 B1 20060424; KR 20030077018 A 20030929; US 2004069382 A1 20040415; WO 02066697 A1 20020829

DOCDB simple family (application)  
**EP 02700640 A 20020220**; CA 2438393 A 20020220; CN 02805402 A 20020220; JP 0201498 W 20020220; JP 2001247306 A 20010816; KR 20037010529 A 20030809; US 46894503 A 20030822