

Title (en)

Device for drawing or stretching (wires, bars, tubes) with a quasi zero wear of the die and the reaching of optimal tribological conditions

Title (de)

Vorrichtung zum Ziehen oder Strecken (Draht, Stange, Rohr) mit einem sehr verschleissarmen Ziehstein und zum Erreichen von optimalen tribologischen Bedingungen

Title (fr)

Dispositif permettant de tréfiler ou étirer (fils, barres, tubes) avec une usure quasi-nulle des filières et l'obtention de conditions tribologiques optimales

Publication

EP 1388379 A1 20040211 (FR)

Application

EP 02356158 A 20020808

Priority

EP 02356158 A 20020808

Abstract (en)

The device uses a threaded tube (1) screwed into a threaded sleeve (2) which itself is held in a large section square (3) welded to the side plates of the slide or soap box. The device uses a threaded tube (1) screwed into a threaded sleeve (2) which itself is held in a large section square (3) welded to the side plates of the slide or soap box. A range of tubes of different internal diameters and substantial thickness are made with a hardness in the range 58HRC (Rockwell C hardness) to 3500HV (Vickers hardness) and have a conical part which matches exactly the angle of the drawing frame. The two surfaces in contact are mirror polished to a roughness of Ra=5/100[deg] of micron. The carbides of the working drawing frame are compacted micrograins using the best HIP (High isostatic pressure) processes. Alternatively, the drawing frame is made of industrial nitride, carbide or boride ceramics with a very high hardness, greater than 1200HV (Vickers), or combined industrial diamond structures of very high hardness and compactness, greater than 1500HV (Vickers). The extruding or drawing lubricants are high viscosity greases or oils (between 20 and 15000 centistokes), with or without the following additives: graphite, molybdenum bisulphide, metal powder or alloys, polymer powder or liquid, or stearate, palmitate, calcium oleate, or sodium doped or otherwise with high pressure elements. The threaded or unthreaded tubes are cylindrical or conical with an angle of 0 to 12[deg] and of any length. The entrance of the tube is equipped with a very hard ring acting as a guide and laminator for the lubricant to engage the very high pressures. In particular for wet drawing, liquid lubricants are used with a non-return valve in the drawing frame.

Abstract (fr)

L'invention concerne un dispositif permettant de tréfiler et étirer les métaux en général, avec une usure quasiment nulle des filières, avec un respect entier de l'état de surface des produits fabriqués. Il est constitué de 3 pièces selon la figure 1: un tube (1) de forte épaisseur et haute durété, terminé par un cône poli-miroir qui vient s'emboiter parfaitement dans le cône de la filière. Le tube est soit cylindrique, soit conique. Le manchon (2) fileté, reçoit ce tube et vient s'appuyer sur la pièce (3) soudée sur les flasques de la couleuse; un entonnoir s'emboite dans l'orifice en (5), y fait couler sur le fil un lubrifiant, extrême pression et forte viscosité, avec ou sans additifs (graphite ou autres). Le point 7 est le siège de très hautes pressions ; donc un film (15) fortement compacté et anti-usure. <IMAGE>

IPC 1-7

B21C 3/14; B21C 9/00; C10M 143/00; C10M 107/00

IPC 8 full level

B21C 3/14 (2006.01); **B21C 9/00** (2006.01); **C10M 171/02** (2006.01)

CPC (source: EP)

B21C 3/14 (2013.01); **B21C 9/005** (2013.01); **C10M 171/02** (2013.01); **C10M 2201/041** (2013.01); **C10M 2201/066** (2013.01);
C10M 2207/126 (2013.01); **C10M 2213/062** (2013.01); **C10N 2010/02** (2013.01); **C10N 2010/04** (2013.01); **C10N 2030/02** (2013.01);
C10N 2030/06 (2013.01); **C10N 2040/24** (2013.01); **C10N 2040/32** (2013.01)

Citation (search report)

- [EL] FR 2820661 A1 20020816 - SABAU ROGER MARCEL [FR]
- [EL] FR 2820660 A1 20020816 - SABAU ROGER MARCEL [FR]
- [EL] FR 2821769 A1 20020913 - SABAU ROGER MARCEL [FR]
- [A] GB 2169232 A 19860709 - NPSP HYDROPLAST OBRABOT METAL
- [A] GB 1507823 A 19780419 - LEE & SONS LTD A
- [A] FR 1139790 A 19570704 - NAT RES DEV
- [A] US 3763680 A 19731009 - STOTT R, et al
- [A] EP 0341688 A1 19891115 - HITACHI LTD [JP]
- [A] FR 2143193 A1 19730202 - BENTELER WERKE AG
- [A] WO 8001765 A1 19800904 - LANGENECKER VERSUCHSANST [AT], et al
- [A] DE 2934222 A1 19810312 - VEREIN DT EISENHUETTENLEUTE
- [A] US 3250103 A 19660510 - JAMES BEAUBIEN STEWART, et al
- [X] PATENT ABSTRACTS OF JAPAN vol. 013, no. 178 (M - 819) 26 April 1989 (1989-04-26)

Cited by

IT201800002835A1; CN103464493A; FR2871078A1; WO2019162796A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

DOCDB simple family (publication)

EP 1388379 A1 20040211

DOCDB simple family (application)

EP 02356158 A 20020808