

Title (en)

HIGH-DUCTILITY ALUMINIUM ALLOY PART CAST UNDER PRESSURE

Title (de)

DRUCKGEGOSSENES BAUTEIL AUS EINER DUKTILEN ALUMINIUM-LEGIERUNG

Title (fr)

PIECE COULEE SOUS PRESSION EN ALLIAGE D'ALUMINIUM A HAUTE DUCTILITE

Publication

EP 1404885 A1 20040407 (FR)

Application

EP 02767556 A 20020709

Priority

- FR 0202394 W 20020709
- FR 0109142 A 20010710
- FR 0115700 A 20011205

Abstract (en)

[origin: WO03006698A1] The invention concerns a safety or structural part cast under pressure made of high-ductility aluminium alloy consisting of (in wt. %): Si 2-6; Mg < 0.40; Cu < 0.30; Zn < 0.30; Fe < 0.50; Ti < 0.30, at least an element for reducing adherence on the mould such as Mn (0.3-2%), Cr (0.1-0.3), Co (0.1-0.3), V (0.1-0.3) and Mo (0.1-0.4), and at least an element modifying eutectics, such as Sr (50-500 ppm), Na (20-100 ppm) and Ca (30-120 ppm); other elements < 0.05 each and < 0.10 in total, the balance being aluminium exhibiting, after T5 tempering at a temperature less than 220 DEG C, a yield strength Rp0.2 > 110 MPa and an elongation A > 10 %.

IPC 1-7

C22C 21/04

IPC 8 full level

B22D 17/00 (2006.01); **C22C 21/02** (2006.01); **C22C 21/04** (2006.01); **C22F 1/00** (2006.01); **C22F 1/043** (2006.01)

CPC (source: EP US)

C22C 21/04 (2013.01 - EP US)

Citation (search report)

See references of WO 03006698A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

DOCDB simple family (publication)

WO 03006698 A1 20030123; CA 2452479 A1 20030123; DE 02767556 T1 20040930; EP 1404885 A1 20040407; FR 2827306 A1 20030117; FR 2827306 B1 20041022; JP 2004536223 A 20041202; US 2005155676 A1 20050721

DOCDB simple family (application)

FR 0202394 W 20020709; CA 2452479 A 20020709; DE 02767556 T 20020709; EP 02767556 A 20020709; FR 0115700 A 20011205; JP 2003512455 A 20020709; US 48079504 A 20041130