

Title (en)

POLYACETAL RESIN COMPOSITION

Title (de)

POLYACETALHARZZUSAMMENSETZUNG

Title (fr)

COMPOSITION DE RESINE DE POLYACETAL

Publication

EP 1508592 B1 20110316 (EN)

Application

EP 03733171 A 20030529

Priority

- JP 0306778 W 20030529
- JP 2002156632 A 20020530

Abstract (en)

[origin: EP1508592A1] A polyacetal resin composition having high rigidity and also excellent in dimensional stability and creep characteristics is provided. A polyacetal resin composition prepared by blending (A) 99.9 to 90 parts by weight of a linear polyacetal resin having a melt index of 1 to 50 g/min obtained by copolymerizing (a) 99.5 to 97.5% by weight of trioxane and (b) 0.5 to 2.5% by weight of a compound selected from a mono-functional cyclic ether compound and a mono-functional cyclic formal compound, with (B) from 0.1 to 10 parts by weight of a branched or crosslinked polyacetal resin having a melt index of 0.1 to 10 g/min obtained by copolymerizing (a) 99.49 to 95.0 % by weight of trioxane, (b) 0.5 to 4.0% by weight of a compound selected from a mono-functional cyclic ether compound and mono-functional cyclic formal compound and (c) 0.01 to 1.0% by weight of a poly-functional glycidyl ether compound with the number of functional groups of 3 to 4, in which (A) and (B) are selected so that the ratio between the melt index of (A) and the melt index of (B) can satisfy the relation of the following formula: <DF NUM="(1)">0.02 </= MIB/MIA </= 1.5 </DF> (where MIA is a melt index of (A) and MIB is a melt index of (B)).

IPC 8 full level

C08L 59/00 (2006.01); **C08L 59/04** (2006.01); **C08G 2/12** (2006.01); **C08G 2/18** (2006.01)

CPC (source: EP US)

C08G 2/12 (2013.01 - EP US); **C08L 59/00** (2013.01 - EP US); **C08L 2205/02** (2013.01 - EP US)

Cited by

EP3480253A4; EP2123709A4; EP2123710A4; EP1887043A1; US2014186562A1; US10181363B2; US7619020B2; US8741202B2; US9109112B2

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PT RO SE SI SK TR

DOCDB simple family (publication)

EP 1508592 A1 20050223; **EP 1508592 A4 20070822**; **EP 1508592 B1 20110316**; AT E502083 T1 20110415; BR 0309170 A 20050426; CA 2483070 A1 20031211; CN 1260291 C 20060621; CN 1461772 A 20031217; DE 60336390 D1 20110428; JP 2003342442 A 20031203; MX PA04011860 A 20050331; US 2005182200 A1 20050818; WO 03102078 A1 20031211

DOCDB simple family (application)

EP 03733171 A 20030529; AT 03733171 T 20030529; BR 0309170 A 20030529; CA 2483070 A 20030529; CN 03137055 A 20030530; DE 60336390 T 20030529; JP 0306778 W 20030529; JP 2002156632 A 20020530; MX PA04011860 A 20030529; US 51033704 A 20041005