

Title (en)

CONVERSION LAYER FOR BASES MADE OF ZINC OR ZINC ALLOYS

Title (de)

KONVERSIONSSCHICHT FÜR AUS ZINK ODER ZINKLEGIERUNGEN BESTEHENDE UNTERGRÜNDE

Title (fr)

COUCHE DE CONVERSION POUR BASES EN ZINC OU EN ALLIAGES DE ZINC

Publication

**EP 1509636 A2 20050302 (DE)**

Application

**EP 03735311 A 20030519**

Priority

- DE 0301617 W 20030519
- DE 10223022 A 20020522

Abstract (en)

[origin: WO03097900A2] The aim of the invention is to create a novel conversion layer, the properties of which regarding breakability, decorative effect, and mechanical abrasion are at least not worse than those of previously known conversion layers. Said aim is achieved by providing the inventive conversion layer with at least one doped siliceous layer that is obtained by applying at least one alkaline siliceous solution which additionally contains aluminum ions and/or ions of at least one B-group element and/or ions of at least one lanthanide and/or ions thereof, which have been complexed with at least one complexing agent, and/or at least one organic polar compound. The novel conversion layer can be used as a corrosion-proof and abrasion-proof protective coating for technical parts and/or for decorative purposes.

IPC 1-7

**C23C 22/60; C23C 22/68; C23C 28/00**

IPC 8 full level

**C23C 22/60** (2006.01)

CPC (source: EP US)

**C23C 22/60** (2013.01 - EP US); **C23C 28/00** (2013.01 - EP US); **C23C 28/04** (2013.01 - EP US); **C23C 2222/10** (2013.01 - EP US);  
**Y10T 428/12729** (2015.01 - EP US)

Citation (search report)

See references of WO 03097900A2

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PT RO SE SI SK TR

DOCDB simple family (publication)

**WO 03097900 A2 20031127; WO 03097900 A3 20040219;** AU 2003236803 A1 20031202; AU 2003236803 A8 20031202;  
DE 10223022 A1 20031211; EP 1509636 A2 20050302; US 2006083942 A1 20060420

DOCDB simple family (application)

**DE 0301617 W 20030519;** AU 2003236803 A 20030519; DE 10223022 A 20020522; EP 03735311 A 20030519; US 51561805 A 20050916