

Title (en)

METHOD OF TREATING THE SURFACE OF AN ARTICLE COMPRISING SILICON WHICH IS CROSS-LINKED BY POLYADDITION

Title (de)

VERFAHREN ZUR BEHANDLUNG DER OBERFLÄCHE EINES GEGENSTANDS MIT DURCH POLYADDITION VERNETZTEM SILIZIUM

Title (fr)

PROCEDE DE TRAITEMENT DE SURFACE D UN ARTICLE COMPORTANT DU SILICONE RETICULE PAR POLYADDITION

Publication

**EP 1513667 A1 20050316 (FR)**

Application

**EP 03760064 A 20030617**

Priority

- FR 0350013 W 20030617
- FR 0207443 A 20020617

Abstract (en)

[origin: FR2840826A1] A method of surface treating an article comprising crosslinked silicone by plasma jet using a homogeneous atmospheric plasma generated by a plasma projection equipment comprising a rotating head comprising one or more plasma nozzles eccentric with respect to the axis of rotation and each capable of generating a plasma jet with an axis parallel to the axis of rotation. The crosslinked silicone is a polyorganosiloxane (POS) crosslinked by polyaddition of -SiH groups onto -Si-alkenyl (preferably vinyl) groups in a silicone preparation comprising: (1) one or more POS with -Si-alkenyl (vinyl) groups; (2) one or more POS with -SiH groups; (3) one or more metallic (preferably platinum) catalysts; (4) optionally one or more POS resins bearing -Si-alkenyl groups; (5) optionally a crosslinking inhibitor; (6) optionally one or more adhesion promoters; (7) optionally one or more mineral fillers; and (8) optionally one or more functional additives to give specific properties. It is disclosed that the equipment used to carry out the treatment is described in US-B-6265690 and is commercially available under the name Plasma Treat (RTM). Independent claims are included for (1) a means of producing an crosslinked silicone article treated by the claimed method by forming a silicone element from the liquid silicone preparation above, crosslinking, surface treating at least part of the surface of the crosslinked element and repeating the first two steps, (2) a method of assembling the crosslinked silicone articles by applying a liquid glue to one or more surfaces, (3) a crosslinked silicone elastomer coating obtainable by the claimed method which has an adhesion force measured by a peel test of 2.7 N/cm, more preferably 2.8 N/cm and most preferably 3-10 N/cm.

IPC 1-7

**B29C 59/14; C08J 7/18**

IPC 8 full level

**B05D 3/04** (2006.01); **B05D 5/10** (2006.01); **B05D 7/02** (2006.01); **B05D 7/26** (2006.01); **B29C 33/40** (2006.01); **B29C 59/00** (2006.01);  
**B29C 59/14** (2006.01); **B29C 65/52** (2006.01); **C08J 5/12** (2006.01); **C08J 7/00** (2006.01); **C08J 7/18** (2006.01); **C08K 3/00** (2006.01);  
**C08K 5/05** (2006.01); **C08K 5/5425** (2006.01); **C08L 83/02** (2006.01); **C08L 83/05** (2006.01); **C08L 83/07** (2006.01); **C09D 183/04** (2006.01);  
**C09D 183/05** (2006.01); **C09D 183/07** (2006.01); **C09J 5/02** (2006.01); **B29K 83/00** (2006.01)

CPC (source: EP US)

**B29C 59/005** (2013.01 - EP US); **B29C 59/14** (2013.01 - EP US); **C08J 5/124** (2013.01 - EP US); **C08J 7/123** (2013.01 - EP US);  
**C09J 5/02** (2013.01 - EP US); **B29C 2059/145** (2013.01 - EP US); **B29K 2083/00** (2013.01 - EP US); **C08J 2383/04** (2013.01 - EP US)

Citation (search report)

See references of WO 03106145A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PT RO SE SI SK TR

DOCDB simple family (publication)

**FR 2840826 A1 20031219; FR 2840826 B1 20050415**; AU 2003255704 A1 20031231; CN 1668448 A 20050914; EP 1513667 A1 20050316;  
JP 2005531654 A 20051020; JP 4255911 B2 20090422; US 2006157453 A1 20060720; US 7423234 B2 20080909; WO 03106145 A1 20031224

DOCDB simple family (application)

**FR 0207443 A 20020617**; AU 2003255704 A 20030617; CN 03816963 A 20030617; EP 03760064 A 20030617; FR 0350013 W 20030617;  
JP 2004513009 A 20030617; US 51834403 A 20030617