

Title (en)

High strength cold rolled steel sheet and method for manufacturing the same

Title (de)

Hochfestes kaltgewalztes Stahlblech und Methode für die Produktion desselben

Title (fr)

Tôle d'acier laminée à froid de haute résistance et méthode pour fabriquer la même chose

Publication

**EP 1568791 A1 20050831 (EN)**

Application

**EP 05003676 A 20050221**

Priority

JP 2004049034 A 20040225

Abstract (en)

The present invention relates to a high strength cold rolled steel sheet consisting of 0.015 % or less of C, 1.5 % or less of Si, 0.4 to 3 % of Mn, 0.15 % or less of P, 0.02 % or less of S, 0.1 to 1 % of sol.Al, 0.01 % or less of N, 0.2 % or less of Ti, by mass %, and the balance of Fe and inevitable impurities. In this steel sheet,  $1 \leq (\text{Ti}/48)/(\text{C}/12 + \text{N}/14)$  is satisfied, in which M represents the content of the element M. Since having the superior deep drawability and the TS of 340 to 590 MPa, the high strength cold rolled steel sheet of the present invention is preferably used for automobiles parts difficult to be press formed, such as a side outer panel and a door inner panel. <IMAGE>

IPC 1-7

**C21D 8/00**; **C21D 9/46**; **C22C 38/00**

IPC 8 full level

**C21D 8/00** (2006.01); **C21D 8/04** (2006.01); **C21D 9/46** (2006.01); **C21D 9/48** (2006.01); **C22C 38/00** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01); **C22C 38/12** (2006.01)

CPC (source: EP KR US)

**C21D 8/0426** (2013.01 - EP KR US); **C21D 8/0436** (2013.01 - KR); **C21D 8/0473** (2013.01 - KR); **C21D 8/0478** (2013.01 - KR); **C22C 38/008** (2013.01 - KR); **C22C 38/02** (2013.01 - EP KR US); **C22C 38/04** (2013.01 - EP KR US); **C22C 38/06** (2013.01 - EP KR US); **C22C 38/14** (2013.01 - KR); **C22C 38/60** (2013.01 - KR); **C21D 8/0436** (2013.01 - EP US); **C21D 8/0473** (2013.01 - EP US); **C21D 8/0478** (2013.01 - EP US)

Citation (search report)

- [XA] US 2003129444 A1 20030710 - MATSUOKA SAIJI [JP], et al
- [X] KR 20010061575 A 20010707 - PO HANG IRON & STEEL [KR]
- [X] KR 20030052355 A 20030627 - POSCO [KR]
- [X] KR 20030052208 A 20030626 - POSCO [KR]
- [XA] PATENT ABSTRACTS OF JAPAN vol. 2000, no. 10 17 November 2000 (2000-11-17)
- [XA] PATENT ABSTRACTS OF JAPAN vol. 2000, no. 10 17 November 2000 (2000-11-17)

Cited by

EP1960562A4; US8353992B2; US8802241B2

Designated contracting state (EPC)

DE FR GB

DOCDB simple family (publication)

**EP 1568791 A1 20050831**; CA 2496212 A1 20050825; CA 2496212 C 20100112; CN 100439544 C 20081203; CN 1661127 A 20050831; KR 20060042036 A 20060512; KR 20070089670 A 20070831; TW 200532032 A 20051001; TW I276692 B 20070321; US 2006037677 A1 20060223

DOCDB simple family (application)

**EP 05003676 A 20050221**; CA 2496212 A 20050203; CN 200510051717 A 20050225; KR 20050013073 A 20050217; KR 20070082656 A 20070817; TW 94105020 A 20050221; US 5036205 A 20050203