

## Title (en)

High tensile strength cold rolled steel sheet having excellent strain age hardening characteristics and the production thereof

## Title (de)

Hochfestes warmgewalztes Stahlblech mit ausgezeichneten Reckalterungseigenschaften

## Title (fr)

Tôle d'acier laminée à froid à haute résistance présentant d'excellentes propriétés de durcissement par vieillissement par l'écrouissage

## Publication

**EP 1571230 B1 20061213 (EN)**

## Application

**EP 05006029 A 20010214**

## Priority

- EP 01904406 A 20010214
- JP 2000053923 A 20000229
- JP 2000151170 A 20000523
- JP 2000162497 A 20000531

## Abstract (en)

[origin: EP1193322A1] The present invention presents a high tensile strength cold rolled steel sheet having excellent formability, impact resistance and strain age hardening characteristics, and the production thereof. As a specific means, a slab having a composition which contains, by mass %, 0.15% or less of C, 0.02% or less of Al, and 0.0050 to 0.0250% of N at N/A1 of 0.3 or higher, and has N in a solid solution state at 0.0010% or more, is first hot rolled at the finish rolling delivery-side temperature of 800 DEG C or above, and is subsequently coiled at the coiling temperature of 750 DEG C or below to prepare a hot rolled plate. Then, after cold rolling, the hot rolled plate is continuously cooled at a temperature from the recrystallization temperature to 900 DEG C at a holding time of 10 to 120 seconds, and is cooled by primary cooling in which the hot rolled plate is cooled to 500 DEG C or below at a cooling rate of 10 to 300 DEG C/s, and furthermore if necessary, by secondary cooling in which a residence time is 300 seconds or less in a temperature range of the primary cooling stopping temperature or higher and 350 DEG C or higher. Provided is a steel sheet containing a ferritic phase having an average crystal grain size of 10  $\mu$  m or less at an area ratio of 50% or more, and if necessary, a martensitic phase at an area ratio of 3% or more as a second phase.

## IPC 8 full level

**C22C 38/00** (2006.01); **C21D 8/02** (2006.01); **C21D 9/46** (2006.01); **C22C 38/02** (2006.01); **C22C 38/04** (2006.01); **C22C 38/06** (2006.01); **C22C 38/12** (2006.01); **C22C 38/22** (2006.01); **C22C 38/38** (2006.01); **C22C 38/58** (2006.01)

## CPC (source: EP KR US)

**C21D 8/0226** (2013.01 - EP US); **C21D 8/0236** (2013.01 - EP US); **C21D 8/0268** (2013.01 - EP US); **C21D 8/0273** (2013.01 - EP US); **C22C 38/001** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP KR US); **C22C 38/06** (2013.01 - EP US); **C22C 38/12** (2013.01 - EP US); **C22C 38/22** (2013.01 - EP US); **C22C 38/38** (2013.01 - EP US); **C21D 2211/005** (2013.01 - EP US); **C21D 2211/008** (2013.01 - EP US)

## Cited by

RU2667947C2; US10995386B2

## Designated contracting state (EPC)

BE DE FR GB IT

## DOCDB simple family (publication)

**EP 1193322 A1 20020403**; **EP 1193322 A4 20040630**; **EP 1193322 B1 20060705**; CA 2368504 A1 20010907; CA 2368504 C 20071218; CN 1145709 C 20040414; CN 1366559 A 20020828; DE 60121266 D1 20060817; DE 60121266 T2 20061109; DE 60125253 D1 20070125; DE 60125253 T2 20070405; DE 60127879 D1 20070524; DE 60127879 T2 20070906; EP 1571229 A1 20050907; EP 1571229 B1 20070411; EP 1571230 A1 20050907; EP 1571230 B1 20061213; KR 100595946 B1 20060703; KR 20010112947 A 20011222; TW 550296 B 20030901; US 2003047256 A1 20030313; US 2003145920 A1 20030807; US 2003188811 A1 20031009; US 6702904 B2 20040309; US 6899771 B2 20050531; US 6902632 B2 20050607; WO 0164967 A1 20010907

## DOCDB simple family (application)

**EP 01904406 A 20010214**; CA 2368504 A 20010214; CN 01801125 A 20010214; DE 60121266 T 20010214; DE 60125253 T 20010214; DE 60127879 T 20010214; EP 05006028 A 20010214; EP 05006029 A 20010214; JP 0101003 W 20010214; KR 20017013657 A 20011025; TW 90103279 A 20010214; US 34116503 A 20030113; US 34116603 A 20030113; US 98051301 A 20011024