

Title (en)
Tin plating electrolyte composition and method for electroplating surfaces with tin

Title (de)
Elektrolytzusammensetzung und Methode zum Elektroplattieren mit Zinn

Title (fr)
Composition électrolytique et procédé de plaquage d'étain

Publication
EP 1580304 B1 20060614 (EN)

Application
EP 04425208 A 20040324

Priority
EP 04425208 A 20040324

Abstract (en)
[origin: EP1580304A1] The invention refers to a composition and method of electrolytic tinning in continuous a steel strip or plate with an electrolyte composition comprising the following components (g/l): Tin (in a form of tin sulfamate) 50-90 Sulfamic acid, free 40-100 Sulfates, in a form of SO_4^{2-} 0-15 Nitrogen-bearing block polymer 1-6 said block polymer being a copolymer of propylene oxide and ethylene oxide with molecular weight of 3950 to 6450 and "number of ethylene oxide links-to-number of propylene oxide links" ratio of 1.4-1.2:1.0 at initial buildup of required number of links from propylene oxide followed by oxyethylation.

IPC 8 full level
C25D 3/32 (2006.01)

CPC (source: EP US)
C25D 3/32 (2013.01 - EP US)

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)
EP 1580304 A1 20050928; EP 1580304 B1 20060614; AT E330045 T1 20060715; CN 1934292 A 20070321; CN 1934292 B 20100512; DE 602004001208 D1 20060727; DE 602004001208 T2 20070516; RU 2006140991 A 20080527; RU 2357014 C2 20090527; US 2007131559 A1 20070614; US 7517443 B2 20090414; WO 2005090646 A1 20050929

DOCDB simple family (application)
EP 04425208 A 20040324; AT 04425208 T 20040324; CN 200580008400 A 20050324; DE 602004001208 T 20040324; EP 2005051390 W 20050324; RU 2006140991 A 20050324; US 59392405 A 20050324