

Title (en)

RADIANT TUBE IN CRACKING FURNACES

Title (de)

STRAHLROHR IN CRACKÖFEN

Title (fr)

TUBE RADIANT POUR FOURS DE CRAQUAGE

Publication

EP 1627093 A1 20060222 (EN)

Application

EP 04733228 A 20040514

Priority

- SE 2004000757 W 20040514
- SE 0301500 A 20030520

Abstract (en)

[origin: WO2004104257A1] Radiant tube in a cracking furnace is disclosed. Hydrocarbons are cracked into ethylene in the tube through which hydrocarbons flow, which tube is heated from the outside to a temperature where cracking occurs. The tube is made from a FeCrAl material containing, in addition to Fe, 10 to 25% by weight of Cr, 1 to 10% by weight of Al and 1.5 to 5% by weight of Mo. Optionally, the material comprises up to a total of 2.2 wt.%, preferably up to 2.0 wt.% and more preferably up to 1.0 wt.%, of one or more alloying materials selected from the group consisting of tantalum, hafnium, zirconium, yttrium, nitrogen, carbon and oxygen.

IPC 1-7

C22C 38/22; C10G 9/20

IPC 8 full level

C10G 9/20 (2006.01)

CPC (source: EP US)

C10G 9/20 (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US); **C22C 38/22** (2013.01 - EP US)

Citation (search report)

See references of WO 2004104257A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)

WO 2004104257 A1 20041202; CN 100365151 C 20080130; CN 1802447 A 20060712; EP 1627093 A1 20060222; JP 2007506866 A 20070322; SE 0301500 D0 20030520; SE 0301500 L 20040615; SE 524010 C2 20040615; US 2005019202 A1 20050127

DOCDB simple family (application)

SE 2004000757 W 20040514; CN 200480013796 A 20040514; EP 04733228 A 20040514; JP 2006532193 A 20040514; SE 0301500 A 20030520; US 84659304 A 20040517