

Title (en)

PIEZOELECTRIC CERAMIC COMPOSITION AND PIEZOELECTRIC ELEMENT INCLUDING THE SAME

Title (de)

PIEZOELEKTRISCHE KERAMIKZUSAMMENSETZUNG UND DIESE ENTHALTENDES PIEZOELEKTRISCHES ELEMENT

Title (fr)

COMPOSITION CERAMIQUE PIEZO-ELECTRIQUE ET ELEMENT PIEZO-ELECTRIQUE COMPRENANT CETTE COMPOSITION

Publication

EP 1630149 A1 20060301 (EN)

Application

EP 04745428 A 20040528

Priority

- JP 2004007392 W 20040528
- JP 2003153426 A 20030529

Abstract (en)

Objects of the present invention are to provide a piezoelectric ceramic composition which contains substantially no lead, which exhibits excellent piezoelectric characteristics, and which has high heat durability; and to provide a piezoelectric element including the composition. The piezoelectric ceramic composition contains M1 (a divalent metallic element, or a metallic element combination formally equivalent to a divalent metallic element); M2 (a tetravalent metallic element, or a metallic element combination formally equivalent to a tetravalent metallic element); and M3 (a metallic element of a sintering aid component), wherein, when these metallic elements constitute the formula $[(1/2)aK_2O-(1/2)bNa_2O-cM1O-(1/2)dNb_2O_5-eM2O_2]$, a, b, c, d, and e in the formula satisfy the following relations: $0 < a < 0.5$, $0 < b < 0.5$, $0 < c < 0.11$, $0.4 < d < 0.56$, $0 < e < 0.12$, $0.4 < a + b + c \leq 0.5$, and $a + b + c + d + e = 1$; and when the total amount of K, Na, Nb, M1, and M2 as reduced to corresponding oxides is 100 parts by mass, the amount of M3 as reduced to M3 oxide is 5 parts by mass or less. The piezoelectric element includes a piezoelectric member formed of the piezoelectric ceramic composition; and a pair of electrodes which are in contact with the piezoelectric member.

IPC 1-7

C04B 35/495; **C04B 35/499**; **H01L 41/187**

IPC 8 full level

C04B 35/495 (2006.01); **H01L 41/187** (2006.01)

CPC (source: EP US)

C04B 35/493 (2013.01 - EP US); **C04B 35/495** (2013.01 - EP US); **C04B 35/6303** (2013.01 - EP US); **H10N 30/8542** (2023.02 - EP US); **B32B 2311/08** (2013.01 - EP US); **C04B 2235/3201** (2013.01 - EP US); **C04B 2235/3203** (2013.01 - EP US); **C04B 2235/3206** (2013.01 - EP US); **C04B 2235/3208** (2013.01 - EP US); **C04B 2235/3213** (2013.01 - EP US); **C04B 2235/3215** (2013.01 - EP US); **C04B 2235/3232** (2013.01 - EP US); **C04B 2235/3244** (2013.01 - EP US); **C04B 2235/3251** (2013.01 - EP US); **C04B 2235/3272** (2013.01 - EP US); **C04B 2235/3275** (2013.01 - EP US); **C04B 2235/3277** (2013.01 - EP US); **C04B 2235/3279** (2013.01 - EP US); **C04B 2235/3281** (2013.01 - EP US); **C04B 2235/3284** (2013.01 - EP US); **C04B 2235/3293** (2013.01 - EP US); **C04B 2235/3294** (2013.01 - EP US); **C04B 2235/3298** (2013.01 - EP US); **C04B 2235/36** (2013.01 - EP US); **C04B 2235/442** (2013.01 - EP US); **C04B 2235/604** (2013.01 - EP US); **C04B 2235/656** (2013.01 - EP US); **C04B 2235/72** (2013.01 - EP US); **C04B 2235/76** (2013.01 - EP US); **C04B 2235/762** (2013.01 - EP US); **C04B 2235/768** (2013.01 - EP US); **C04B 2237/345** (2013.01 - EP US); **C04B 2237/408** (2013.01 - EP US)

Cited by

WO2015115279A1; WO2008122458A1; US7754095B2; US7910016B2

Designated contracting state (EPC)

DE FR GB IT

DOCDB simple family (publication)

EP 1630149 A1 20060301; **EP 1630149 A4 20090121**; **EP 1630149 B1 20131009**; BR PI0409353 A 20060425; BR PI0409353 B1 20171031; CN 100337980 C 20070919; CN 1787981 A 20060614; US 2007120446 A1 20070531; WO 2004106264 A1 20041209

DOCDB simple family (application)

EP 04745428 A 20040528; BR PI0409353 A 20040528; CN 200480011585 A 20040528; JP 2004007392 W 20040528; US 55838304 A 20040528