

Title (en)  
METHOD FOR PREPARING POLYETHOXYLATED POLYOLS FROM SOLID POLYOLS AT NORMAL TEMPERATURE AND COMPOSITION USED

Title (de)  
VERFAHREN ZUR HERSTELLUNG POLYETHOXYLICHTER POLYOLE AUS FESTEN POLYOLEN BEI NORMALER TEMPERATUR UND VERWENDETE ZUSAMMENSETZUNG

Title (fr)  
PROCEDE DE PREPARATION DE POLYOLS POLYETHOXYLES A PARTIR DE POLYOLS SOLIDES A TEMPERATURE ORDINAIRE ET COMPOSITION MISE EN OEUVRE

Publication  
**EP 1646601 A1 20060419 (FR)**

Application  
**EP 04767608 A 20040707**

Priority  
• FR 2004001773 W 20040707  
• FR 0350331 A 20030715

Abstract (en)  
[origin: FR2857662A1] Composition, liquid at normal temperature and pressure, comprising a mixture of a polyoxylated polyol and polyoxylated trimethylolpropane, obtained by a reaction at less than 10 bars and 180[deg]C or less of a mixture of more than 50% wt. of a polyol of melting point greater than 180[deg]C, preferably greater than 200[deg]C, and less than 50% of trimethylolpropane (TMP), with an alkylene oxide, gaseous at ambient temperature and pressure. An independent claim is also included for the preparation of the liquid composition and of acrylic or methacrylic esters using the composition.

IPC 1-7  
**C07C 43/13**; **C08G 65/08**

IPC 8 full level  
**C07C 43/11** (2006.01); **C07C 67/08** (2006.01); **C08G 65/26** (2006.01); **C08L 71/02** (2006.01)

CPC (source: EP)  
**C07C 43/11** (2013.01); **C07C 67/08** (2013.01); **C08G 65/2609** (2013.01); **C08L 71/02** (2013.01)

C-Set (source: EP)  
1. **C07C 67/08** + **C07C 69/54**  
2. **C08L 71/02** + **C08L 2666/22**

Citation (search report)  
See references of WO 2005007604A1

Designated contracting state (EPC)  
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)  
**FR 2857662 A1 20050121**; **FR 2857662 B1 20080613**; EP 1646601 A1 20060419; WO 2005007604 A1 20050127

DOCDB simple family (application)  
**FR 0350331 A 20030715**; EP 04767608 A 20040707; FR 2004001773 W 20040707