

Title (en)

METHOD FOR THE GENERATION OF HOT STRIPS OF LIGHT GAUGE STEEL

Title (de)

VERFAHREN ZUM ERZEUGEN VON WARMBÄNDERN AUS LEICHTBAUSTAHL

Title (fr)

PROCEDE POUR PRODUIRE DES FEUILLARDS A CHAUD A PARTIR D'UN ACIER LEGER

Publication

EP 1699582 B1 20131211 (DE)

Application

EP 04802997 A 20041222

Priority

- DE 2004002817 W 20041222
- DE 10361952 A 20031223
- DE 102004061284 A 20041214

Abstract (en)

[origin: WO2005061152A1] The invention relates to a method for the generation of hot strips, made from a workable light gauge steel which is particularly easy to cold deep draw, comprising the main elements Si, Al and Mn, with high tensile strength and good TRIP and/or TWIP properties. The mass % are as follows for C 0.04 to < 1.0, Al 0.05 to < 4.0, Si 0.05 TO < 6.0; Mn 9.0 to < 30.0, the rest being iron with the usual elements present in steel. The melt is cast in a horizontal strip casting unit, close to the final measurements, free of bends and with a killed-flow to give a pre-strip in the range of 6 to 15 mm and then introduced to a further processing.

IPC 8 full level

B22D 11/045 (2006.01); **B22D 11/06** (2006.01); **C21D 8/02** (2006.01); **C21D 8/04** (2006.01); **C22C 38/00** (2006.01)

CPC (source: EP KR US)

B22D 11/045 (2013.01 - EP KR US); **B22D 11/0605** (2013.01 - EP KR US); **C21D 8/0405** (2013.01 - EP KR US);
C21D 8/0415 (2013.01 - EP KR US); **C21D 8/0426** (2013.01 - KR); **C22C 38/02** (2013.01 - EP KR US); **C22C 38/04** (2013.01 - EP KR US);
C22C 38/06 (2013.01 - EP KR US); **C21D 8/0426** (2013.01 - EP US)

Cited by

DE102014009534A1; WO2015197412A1

Designated contracting state (EPC)

DE

DOCDB simple family (publication)

WO 2005061152 A1 20050707; EP 1699582 A1 20060913; EP 1699582 B1 20131211; KR 101178775 B1 20120907;
KR 20070007034 A 20070112; US 2007289717 A1 20071220; US 7806165 B2 20101005

DOCDB simple family (application)

DE 2004002817 W 20041222; EP 04802997 A 20041222; KR 20067012471 A 20041222; US 59678104 A 20041222