

Title (en)  
METHOD FOR PRODUCING Al-Mg-Si BASED ALUMINUM ALLOY PLATE EXCELLENT IN BAKE-HARDENABILITY

Title (de)  
VERFAHREN ZUR HERSTELLUNG EINER AUF AL-MG-SI BASIERENDEN ALUMINIUMLEGIERUNGSPLATTE MIT HERVORRAGENDER BAKE-HARDENABILITY

Title (fr)  
PROCEDE DE PRODUCTION DE PLAQUES D'ALLIAGE D'AL-MG-SI PRESENTANT UNE EXCELLENTE CAPACITE DE DURCISSEMENT THERMIQUE

Publication  
**EP 1715067 A4 20071031 (EN)**

Application  
**EP 04807567 A 20041222**

Priority  
• JP 2004019210 W 20041222  
• JP 2003432073 A 20031226

Abstract (en)  
[origin: EP1715067A1] Summary [Objectives] Strengthening, cost reduction, and improvement of press formability and bake hardenability of aluminum alloy sheets. [Means for achieving objectives] A manufacturing method for Al-Mg-Si aluminum alloy sheet with excellent bake hardenability, characterized by twin belt casting a molten Al-Mg-Si aluminum alloy containing Mg: 0.3 - 1.0 wt%, Si: 0.3 - 1.5 wt%, Cu: 1.0 wt% or below (including 0%), and Fe: 1.2 wt% or below (including 0%), and containing Mn: 0.1 - 0.7 wt% and/or Cr: 0.1 - 0.3% according to need, and the remnant being Al at an average cooling rate of 20 degrees C or above, and at that time, making the temperature of the ingot as it comes out of the casting machine 250 degrees C or below, and then rolling to the final sheet thickness by cold rolling only and without homogenization or hot rolling, and solution treatment being done in a continuous annealing furnace.

IPC 8 full level  
**C22C 1/05** (2006.01); **B22D 11/00** (2006.01); **B22D 11/06** (2006.01); **B22D 11/12** (2006.01); **B22D 11/22** (2006.01); **C22C 21/02** (2006.01); **C22C 21/06** (2006.01); **C22C 21/08** (2006.01); **C22F 1/05** (2006.01); **B21B 3/00** (2006.01)

CPC (source: EP KR US)  
**B22D 11/003** (2013.01 - EP US); **B22D 11/0605** (2013.01 - EP US); **B22D 11/22** (2013.01 - EP US); **C22C 1/05** (2013.01 - KR); **C22C 21/08** (2013.01 - EP KR US); **C22F 1/05** (2013.01 - EP US); **B21B 2003/001** (2013.01 - EP US)

Citation (search report)  
• [E] EP 1614760 A1 20060111 - NIPPON LIGHT METAL CO [JP]  
• [X] JP S62207851 A 19870912 - SKY ALUMINIUM  
• See references of WO 2005064025A1

Cited by  
EP2489755A4; DE102008008326A1; EP2822717A4; US2011265606A1; US9096915B2; EP2822716A4; WO2008078399A1; EP2553131B1

Designated contracting state (EPC)  
DE FR GB

DOCDB simple family (publication)  
**EP 1715067 A1 20061025; EP 1715067 A4 20071031**; CA 2551599 A1 20050714; CN 1922336 A 20070228; JP WO2005064025 A1 20080417; KR 20060135711 A 20061229; TW 200530406 A 20050916; US 2007144630 A1 20070628; WO 2005064025 A1 20050714

DOCDB simple family (application)  
**EP 04807567 A 20041222**; CA 2551599 A 20041222; CN 200480042140 A 20041222; JP 2004019210 W 20041222; JP 2005516601 A 20041222; KR 20067014313 A 20060714; TW 93138422 A 20041210; US 58420004 A 20041222