

Title (en)  
ALUMINIUM ALLOY FOR CASTING, HAVING HIGH RIGIDITY AND LOW LINER EXPANSION COEFFICIENT

Title (de)  
ALUMINIUMGUSSLEGIERUNG MIT HOHER STEIFIGKEIT UND KLEINEM LINEAREM AUSDEHNUNGSKOEFFIZIENTEN

Title (fr)  
ALLIAGE D'ALUMINIUM POUR LE MOULAGE, POSSEDANT UNE RIGIDITE ELEVEE ET UN COEFFICIENT DE DILATATION LINEIQUE FAIBLE

Publication  
**EP 1728882 A4 20071031 (EN)**

Application  
**EP 05726972 A 20050323**

Priority  
• JP 2005005225 W 20050323  
• JP 2004084256 A 20040323

Abstract (en)  
[origin: EP1728882A2] [Objectives] An aluminum alloy for casting that realizes high rigidity and a low linear expansion coefficient, and at the same time, does not have a high cost, and has few restrictions at the time of recycling. [Means for Achieving Objectives] An aluminum alloy for casting with excellent rigidity and having a low coefficient of linear expansion containing 13-25% by mass of silicon, 2-8% by mass of copper, 0.5-3% by mass of iron, 0.3-3% by mass of manganese, 0.001-0.02% by mass of phosphorus, and the remainder comprising aluminum and inevitable impurities, wherein the total amount of iron and manganese is 3.0% by mass or greater. Said alloy may further contain 0.5-6% by mass of nickel, and the total amount of iron, manganese, and nickel may be 3.0% by mass or greater. Further, said alloy may further contain one or more of 0.1-1.0% by mass of chromium, 0.05-1.5% by mass of magnesium, 0.01-1.0% by mass of titanium, 0.0001-1.0% by mass of boron, 0.1-1.0% by mass of zirconium, 0.1-1.0% by mass of vanadium, or 0.01-1.0% by mass of molybdenum.

IPC 8 full level  
**B22D 17/00** (2006.01); **C22C 21/02** (2006.01); **B22D 11/06** (2006.01); **B22D 11/124** (2006.01); **C22C 21/06** (2006.01); **C22F 1/05** (2006.01)

CPC (source: EP KR US)  
**B22D 11/06** (2013.01 - KR); **B22D 11/0605** (2013.01 - EP US); **B22D 11/124** (2013.01 - EP US); **B22D 17/00** (2013.01 - KR); **C22C 21/02** (2013.01 - EP KR US); **C22C 21/06** (2013.01 - KR); **C22F 1/05** (2013.01 - EP US)

Citation (search report)  
• [X] JP 2000054053 A 20000222 - TOYOTA MOTOR CORP  
• [X] SU 431252 A1 19740605  
• [XD] JP H03199336 A 19910830 - RYOBI LTD  
• [X] JP H0273935 A 19900313 - HONDA MOTOR CO LTD  
• [AD] JP H01180938 A 19890718 - RYOBI LTD  
• [A] FR 2788788 A1 20000728 - PECHINEY ALUMINIUM [FR]  
• [A] JP 2002206131 A 20020726 - NIPPON LIGHT METAL CO  
• [A] FR 2489846 A1 19820312 - COMALCO LTD [AU]  
• [A] WO 9713882 A1 19970417 - OPTICAST AB [SE], et al  
• [A] EP 0362086 A1 19900404 - PECHINEY RECHERCHE [FR] & DATABASE WPI Derwent World Patents Index; AN 1975-31893w, XP002451317  
• [A] HATCH J E: "ALUMINUM", 1984, ALUMINUM. PROPERTIES AND PHYSICAL METALLURGY, OHIO, AMERICAN SOCIETY FOR METALS, US, PAGE 350, XP002451306

Cited by  
CN111926222A; CN105838934A; CN103231038A; US2015315688A1; US9834828B2; WO2013050356A1

Designated contracting state (EPC)  
DE FR GB

DOCDB simple family (publication)  
**EP 1728882 A2 20061206; EP 1728882 A4 20071031; EP 1728882 B1 20130918**; JP 2005272868 A 20051006; JP 4665413 B2 20110406; KR 20060130753 A 20061219; MY 139116 A 20090828; US 2007193663 A1 20070823; US 2010296964 A1 20101125; WO 2005090624 A2 20050929

DOCDB simple family (application)  
**EP 05726972 A 20050323**; JP 2004084256 A 20040323; JP 2005005225 W 20050323; KR 20067021516 A 20061017; MY PI20051266 A 20050322; US 59333805 A 20050323; US 84885910 A 20100802