

Title (en)

METHOD FOR MAKING HIGH-TENACITY AND HIGH-FATIGUE STRENGTH ALUMINIUM ALLOY PRODUCTS

Title (de)

VERFAHREN ZUR HERSTELLUNG HOCHFESTER UND ERMÜDUNGSFESTER ALUMINIUMLEGIERUNGSPRODUKTE

Title (fr)

PROCEDE DE FABRICATION DE PRODUITS EN ALLIAGE D'ALUMINIUM A HAUTE TENACITE ET HAUTE RESISTANCE A LA FATIGUE

Publication

EP 1766102 B1 20081210 (FR)

Application

EP 05778801 A 20050622

Priority

- FR 2005001572 W 20050622
- FR 0406957 A 20040625

Abstract (en)

[origin: WO2006010817A1] The invention concerns a method for making high tenacity and high-fatigue strength welded products of aluminium alloy of type Al-Cu, Al-Cu-Mg or Al-Zn-Cu-Mg, containing between 0,005 and 0,1 % of barium. Such an alloy exhibits greater tenacity than a corresponding product without barium.

IPC 8 full level

C22F 1/053 (2006.01); **B64C 1/06** (2006.01); **B64C 3/18** (2006.01); **C22C 21/00** (2006.01); **C22C 21/10** (2006.01); **C22C 21/12** (2006.01); **C22C 21/14** (2006.01); **C22C 21/16** (2006.01); **C22C 21/18** (2006.01); **C22F 1/057** (2006.01)

CPC (source: EP US)

C22C 21/10 (2013.01 - EP US); **C22C 21/12** (2013.01 - EP US); **C22C 21/14** (2013.01 - EP US); **C22C 21/16** (2013.01 - EP US)

Cited by

EP3026136A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)

FR 2872172 A1 20051230; FR 2872172 B1 20070427; AT E417136 T1 20081215; BR PI0512590 A 20080325; CA 2570618 A1 20060202; CN 100564571 C 20091202; CN 1977063 A 20070606; DE 602005011619 D1 20090122; EP 1766102 A1 20070328; EP 1766102 B1 20081210; US 2007243097 A1 20071018; WO 2006010817 A1 20060202

DOCDB simple family (application)

FR 0406957 A 20040625; AT 05778801 T 20050622; BR PI0512590 A 20050622; CA 2570618 A 20050622; CN 200580021275 A 20050622; DE 602005011619 T 20050622; EP 05778801 A 20050622; FR 2005001572 W 20050622; US 57118905 A 20050622