

Title (en)
POLYETHER BLOCK AMIDE FOAM

Title (de)
POLYETHERBLOCKAMID-SCHAUMSTOFF

Title (fr)
MOUSSE AMIDE A BLOCS POLYETHER

Publication
EP 1828290 A1 20070905 (EN)

Application
EP 05798154 A 20051019

Priority

- EP 2005011253 W 20051019
- EP 04024833 A 20041019
- US 63237804 P 20041202
- EP 05798154 A 20051019

Abstract (en)
[origin: EP1650255A1] The present invention concerns a crosslinked foam of a copolymer having polyamide blocks and polyether blocks and a density from 20 to 700 kg/m³. Density is measured according to Method ISO 845. Advantageously the density is from 70 kg/m³ to 400 kg/m³. Advantageously the cell size is from 0.05 to 2.0 mm, preferably from 0.1 mm to 1.0 mm. Advantageously the cells are closed. Preferably the foam does not undergo any further mechanical or thermal treatment. This foam has many advantages and specific features: The compressive strength is from 90 to 170 kPa, preferably from 110 to 150 kPa (measured on foam of 240 kg/m³, at 25% deflection, method according to ISO 844). The shore hardness O is from 20 to 34, preferably from 23 to 32 (measured on foam of 240 kg/m³, internal method). The thermal conductivity is from 0.038 to 0.058 W/m[°]K, preferably from 0.043 to 0.053 W/m[°]K (measured on foam of 240 kg/m³, method according to ISO 2581) The energy return is 28 to 40 cm, preferably 31 to 37 cm (measured on foam of 240 kg/m³, method according to ISO 8307). The water vapour transmission is 500 to 10000 g/m²/day, preferably 1000 to 3500 g/m²/day (measured on foam of 240 kg/m³, 2.5 mm thickness, method according to ASTM E96 BW) provided there are enough hydrophilic polyether blocks.

IPC 8 full level
C08J 9/00 (2006.01)

CPC (source: EP KR)
C08J 9/0061 (2013.01 - EP); **C08J 9/04** (2013.01 - EP KR); **C08J 9/228** (2013.01 - KR); **C08L 87/005** (2013.01 - EP KR); **C08J 2201/024** (2013.01 - EP); **C08J 2201/03** (2013.01 - EP); **C08J 2205/052** (2013.01 - EP KR); **C08J 2377/00** (2013.01 - EP); **C08J 2387/00** (2013.01 - EP KR); **C08J 2423/00** (2013.01 - EP)

Citation (search report)
See references of WO 2006045513A1

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)
EP 1650255 A1 20060426; CN 101044196 A 20070926; EP 1828290 A1 20070905; JP 2008517122 A 20080522; KR 20070092204 A 20070912; TW 200621847 A 20060701; WO 2006045513 A1 20060504; WO 2006045513 A8 20070531

DOCDB simple family (application)
EP 04024833 A 20041019; CN 200580035751 A 20051019; EP 05798154 A 20051019; EP 2005011253 W 20051019; JP 2007537204 A 20051019; KR 20077010556 A 20070509; TW 94136455 A 20051019