

Title (en)

Procedure and device for liming fibres around a blast pipe

Title (de)

Verfahren und Vorrichtung zur Beleimung von Fasern im Bereich eines Blasrohrs

Title (fr)

Procédé et dispositif destinés à relier des fibres dans la zone d'un tube de soufflage

Publication

EP 1862214 A3 20080702 (DE)

Application

EP 07010867 A 20070601

Priority

DE 102006026124 A 20060603

Abstract (en)

[origin: EP1862214A2] The coating of fibers with a component of a multi-component bonding agent (11) for the production of molded bodies from fiberboard glued with the bonding agent, in which the fibers suspended in water steam is passed through by a blow tube (3), that a refiner (2) delivering the fibers in hot and damp condition under pressure relaxation in the blow tube stretches to a dryer for the fiber connecting at the blow tube, and the component of the bonding agent is sprayed on the fibers in an area of the blow tube without an additional atomization medium. The coating of fibers with a component of a multi-component bonding agent (11) for the production of molded bodies from fiberboard glued with the bonding agent, in which the fibers suspended in water steam is passed through by a blow tube (3), that a refiner (2) delivering the fibers in hot and damp condition under pressure relaxation in the blow tube stretches to a dryer for the fiber connecting at the blow tube, and the component of the bonding agent is sprayed on the fibers in an area of the blow tube without an additional atomization medium. The fibers suspended in the water steam are led by a nozzle-shaped constriction of the blow tube. The component is sprayed on the fibers in the area of the constriction on the axis of the blow tube in a main movement direction of the fibers. The nozzle-shaped constriction is intended at the exit of the refiner or at the entrance of the dryer. The component is sprayed on the fibers before a closest point of the constriction. A pressure ratio over the constriction of the blow tube is adjusted in a range of greater than 1-4. The component is pre-sputtered before impacting on the water steam suspension of the fibers. A further component of the multi-component bonding agent is applied on the fibers after the drier. An independent claim is included for device for coating of fibers.

IPC 8 full level

B01F 5/04 (2006.01); **B01F 5/06** (2006.01); **B27N 1/02** (2006.01)

CPC (source: EP)

B01F 25/3131 (2022.01); **B01F 25/433** (2022.01); **B01F 25/4335** (2022.01); **B27N 1/02** (2013.01); **B01F 23/21** (2022.01); **B01F 23/57** (2022.01); **B01F 2025/913** (2022.01)

Citation (search report)

- [XDAY] DE 1632450 A1 19701210 - DRAISWERKE GMBH
- [XDAY] EP 0078960 A1 19830518 - BAYER AG
- [XA] US 6082713 A 20000704 - KING LEONARD TONY [US]
- [XAY] DE 1208294 B 19660105 - GUBELA CHEMIE K G

Cited by

EP2213431A3; CN114514101A; DE202008015419U1; WO2011036200A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

Designated extension state (EPC)

AL BA HR MK RS

DOCDB simple family (publication)

EP 1862214 A2 20071205; EP 1862214 A3 20080702; DE 102006026124 A1 20071206

DOCDB simple family (application)

EP 07010867 A 20070601; DE 102006026124 A 20060603