

Title (en)  
OIL WELL SEAMLESS PIPE HAVING EXCELLENT SULFIDE STRESS CRACKING RESISTANCE AND METHOD FOR MANUFACTURING AN OIL WELL SEAMLESS STEEL PIPE

Title (de)  
ÖLBOHRUNGSNAHTLOSENSTAHLROHR MIT HOHER SULFID-SPANNUNGSRISS-BESTÄNDIGKEIT UND VERFAHREN ZUR HERSTELLUNG EINES ÖLBOHRUNGSNAHTLOSENSTAHLROHRES

Title (fr)  
TUYAU DE Puits DE PÉTROLE EN ACIER SANS SOUDURE AYANT UNE EXCELLENTE RÉSISTANCE À LA CORROSION FISSURANTE PAR L'HYDROGÈNE SULFURÉ ET PROCÉDÉ À FABRIQUER UN TUYAU DE Tuits DE PÉTROLE EN ACIER SANS SOUDURE

Publication  
**EP 1862561 A1 20071205 (EN)**

Application  
**EP 06728622 A 20060303**

Priority  
• JP 2006304143 W 20060303  
• JP 2005086995 A 20050324

Abstract (en)  
A steel for an oil well pipe, having high strength and excellent SSC resistance, and a method for producing a seamless steel pipe for an oil well having these characteristics. The steel consists of, by mass %, C: 0.30 to 0.60%, Si: 0.05 to 0.5%, Mn: 0.05 to 1.0%, Al: 0.005 to 0.10%, Cr+Mo: 1.5 to 3.0%, wherein Mo is 0.5% or more, V: 0.05 to 0.3%, Nb: 0 to 0.1 %, Ti: 0 to 0.1%, Zr: 0 to 0.1%, N (nitrogen): 0 to 0.03%, Ca: 0 to 0.01%, and the balance Fe and impurities. Among impurities P is 0.025% or less, S is 0.01% or less, B is 0.0010% or less and O (oxygen) is 0.01% or less. The method is characterized by heating a steel ingot having the above chemical composition at 1150 °C or more; producing a seamless steel pipe by hot working; water-cooling the pipe to a temperature in a range of 400 to 600 °C immediately after finishing the working; and subjecting the pipe to a heat treatment for bainite isothermal transformation in a range of 400 to 600 °C. A complementary heating treatment may be performed in a range of 900 to 950 °C before water-cooling.

IPC 8 full level  
**C21D 8/10** (2006.01); **C22C 38/00** (2006.01)

CPC (source: EP NO US)  
**C21D 8/00** (2013.01 - NO); **C21D 8/10** (2013.01 - NO); **C21D 8/105** (2013.01 - EP US); **C21D 9/08** (2013.01 - EP NO US); **C21D 9/085** (2013.01 - NO); **C22C 38/00** (2013.01 - NO); **C22C 38/002** (2013.01 - EP US); **C22C 38/02** (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/12** (2013.01 - EP NO US); **C22C 38/14** (2013.01 - EP US); **C22C 38/22** (2013.01 - EP US); **C22C 38/24** (2013.01 - EP US)

Cited by  
WO2010100020A1; WO2011151186A1; EP2865775A4; EP3026139A4; EP3524706A4; EP2915896A4; FR2939449A1; EP1911857A4; EA020245B1; FR2960883A1; AU2011260493B2; EA023196B1; EP3508603A4; EP3231884A4; EP3760754A4; US10407758B2; US10036078B2; EP3425078A4; EP3778956A4; FR2942808A1; EA019473B1; EP3778957A4; WO2010066584A1; WO2014082945A1; US11060160B2; US9394594B2; US10640857B2; US9273383B2

Designated contracting state (EPC)  
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)  
**EP 1862561 A1 20071205; EP 1862561 A4 20090826; EP 1862561 B1 20170920; EP 1862561 B9 20171122**; AR 052614 A1 20070321; AU 2006225855 A1 20060928; AU 2006225855 B2 20090827; BR PI0609443 A2 20100406; BR PI0609443 B1 20171121; CA 2599868 A1 20060928; CA 2599868 C 20110712; CN 101146924 A 20080319; CN 101146924 B 20100811; EA 011363 B1 20090227; EA 200702066 A1 20080228; JP 2006265657 A 20061005; JP 4609138 B2 20110112; NO 20074205 L 20071023; NO 343350 B1 20190204; UA 88359 C2 20091012; US 2008017284 A1 20080124; US 8617462 B2 20131231; WO 2006100891 A1 20060928

DOCDB simple family (application)  
**EP 06728622 A 20060303**; AR P060101060 A 20060317; AU 2006225855 A 20060303; BR PI0609443 A 20060303; CA 2599868 A 20060303; CN 200680009528 A 20060303; EA 200702066 A 20060303; JP 2005086995 A 20050324; JP 2006304143 W 20060303; NO 20074205 A 20070816; UA A200711659 A 20060303; US 90243207 A 20070921