

Title (en)

Workpiece made of a high-strength steel alloy and its use

Title (de)

Werkstück aus einer hochfesten Stahllegierung und dessen Verwendung

Title (fr)

Pièce en acier à haute résistance mécanique et sa utilisation

Publication

**EP 1881083 B1 20091230 (DE)**

Application

**EP 07014185 A 20070719**

Priority

DE 102006033813 A 20060719

Abstract (en)

[origin: EP1881083A1] Workpiece made from a high strength steel alloy contains (in wt.%) 0.11-0.18 carbon, 0.10-0.30 silicon, 1.60-2.20 manganese, less than 0.0015 phosphorus, less than 0.010 sulfur, 1.00-2.00 chromium, less than 0.020 nitrogen, 0.020-0.060 niobium, 0.001-0.004 boron, 0.001-0.050 titanium and a balance of iron. A semi-finished product in the form of sheet metal or tube with a ductile ferritic-perlitic structure is heat treated by austenizing, cooling in air and then optionally tempered. The workpiece has a tensile strength Rm of more than 1.200 MPa at a fraction elongation A5 of more than 12 %.

IPC 8 full level

**C22C 38/00** (2006.01)

CPC (source: EP)

**C21D 1/25** (2013.01); **C21D 1/56** (2013.01); **C22C 38/02** (2013.01); **C22C 38/26** (2013.01); **C22C 38/28** (2013.01); **C22C 38/32** (2013.01); **C22C 38/38** (2013.01); **C21D 2211/002** (2013.01)

Cited by

CZ305430B6; DE102011012428B4; CN108474080A; CN114174542A; US11384415B2; WO2017085135A1; WO2018220430A1; WO2018220598A1; US11629388B2; WO2017006144A1; WO2017006159A1; EP3591079A1; EP3604564A1; US11319610B2; EP4234746A2; US11814696B2

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

DOCDB simple family (publication)

**EP 1881083 A1 20080123**; **EP 1881083 B1 20091230**; AT E453733 T1 20100115; DE 102007033950 A1 20080131; DE 502007002467 D1 20100211

DOCDB simple family (application)

**EP 07014185 A 20070719**; AT 07014185 T 20070719; DE 102007033950 A 20070719; DE 502007002467 T 20070719