

Title (en)
NON-ORIENTED ELECTRICAL STEEL SHEETS WITH IMPROVED MAGNETIC PROPERTY AND METHOD FOR MANUFACTURING THE SAME

Title (de)
NICHTORIENTIERTE ELEKTROSTAHLBLECHE MIT VERBESSERTER MAGNETISCHER EIGENSCHAFT UND HERSTELLUNGSVERFAHREN
DAFÜR

Title (fr)
FEUILLES D'ACIER MAGNETIQUES NON ORIENTÉES POSSEDDANT DES PROPRIÉTÉS MAGNETIQUES AMÉLIORÉES ET LEUR PROCÉDÉ
DE FABRICATION

Publication
EP 1966403 A4 20100714 (EN)

Application
EP 06835238 A 20061218

Priority
• KR 2006005521 W 20061218
• KR 20050130388 A 20051227
• KR 20060127865 A 20061214

Abstract (en)
[origin: WO2007074987A1] The present invention relates to a non-oriented electrical steel sheet, widely used as an iron core in electric devices, and to a method of manufacturing the same. The non-oriented electrical sheet includes 0.004 wt. % or less C; 1.0-3.5 wt. % Si; 0.02 wt. % or less P ; 0.001 wt. % or less S ; 0.2~2.5 wt. % Al; 0.003 wt. % or less N; 0.004 wt. % or less Ti; Mn, in which the amount of thereof is represented by the following formula (1): $0.10 + 100 \times S(\text{wt. \%}) = Mn(\text{wt. \%}) = 0.21 + 200 \times S(\text{wt. \%}) - (1)$; a balance of iron; and inevitable impurities. According to the present invention, final magnetic properties are greatly improved because fine precipitates are formed by S, the amount of Mn can be suitably determined in order to inhibit the formation of the fine precipitates, the formation of fine precipitate CuS is inhibited because precipitates CuS, MnS are formed by adding Sn, Ni and Cu, and a texture, which determines a temperature of annealing a hot rolled steel plate and magnetic properties, is controlled, thereby manufacturing an inexpensive and optimum non-oriented electrical steel sheet.

IPC 8 full level
C22C 38/00 (2006.01); **C21D 8/12** (2006.01)

CPC (source: EP US)
C21D 8/1244 (2013.01 - EP US); **C21D 8/1261** (2013.01 - EP US); **C21D 8/1272** (2013.01 - EP US); **C22C 38/004** (2013.01 - EP US);
C22C 38/02 (2013.01 - EP US); **C22C 38/04** (2013.01 - EP US); **C22C 38/06** (2013.01 - EP US); **C22C 38/08** (2013.01 - EP US);
C22C 38/14 (2013.01 - EP US); **C22C 38/16** (2013.01 - EP US)

Citation (search report)
• [XA] JP H11293425 A 19991026 - NIPPON KOKAN KK
• [XD] US 6139650 A 20001031 - ODA YOSHIHIKO [JP], et al
• [A] US 5102478 A 19920407 - HOSOYA YOSHIHIRO [JP], et al
• [A] JP H1112699 A 19990119 - SUMITOMO METAL IND
• [A] JP 2004002954 A 20040108 - NIPPON STEEL CORP
• See references of WO 2007074987A1

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI SK TR

DOCDB simple family (publication)
WO 2007074987 A1 20070705; EP 1966403 A1 20080910; EP 1966403 A4 20100714; JP 2009518546 A 20090507;
US 2008260569 A1 20081023; US 7763122 B2 20100727

DOCDB simple family (application)
KR 2006005521 W 20061218; EP 06835238 A 20061218; JP 2008545502 A 20061218; US 9520906 A 20061218