

Title (en)
Equestrian floor and method of producing same

Title (de)
Reitboden und sein Herstellungsverfahren

Title (fr)
Sol équestre et son procédé de réalisation

Publication
EP 2009179 B1 20110406 (FR)

Application
EP 08305346 A 20080627

Priority
FR 0704698 A 20070629

Abstract (en)
[origin: EP2009179A1] The floor has a base layer (2) arranged on a stabilized floor base (1) and constituted of compacted rubber aggregates connected by a binder e.g. polymerizable resin. The base layer has a thickness ranging between 2-12 millimeters, and comprises a rough upper surface (6) provided with multidirectional striations. A surface layer (3) is constituted of free rubber aggregates, and has a thickness ranging between 10-50 millimeters, where the surface layer covers the base layer. The aggregates are obtained by recycling worn tires. An independent claim is also included for a method of forming an equestrian floor.

IPC 8 full level
E01C 13/06 (2006.01)

CPC (source: EP)
E01C 13/065 (2013.01)

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT RO SE SI SK TR

DOCDB simple family (publication)
EP 2009179 A1 20081231; EP 2009179 B1 20110406; AT E504697 T1 20110415; DE 602008005956 D1 20110519; ES 2364217 T3 20110829; FR 2918083 A1 20090102; FR 2918083 B1 20110225; PL 2009179 T3 20111230; PT 2009179 E 20110712

DOCDB simple family (application)
EP 08305346 A 20080627; AT 08305346 T 20080627; DE 602008005956 T 20080627; ES 08305346 T 20080627; FR 0704698 A 20070629; PL 08305346 T 20080627; PT 08305346 T 20080627