

Title (en)

MOLD FLUX AND CONTINUOUS CASTING METHOD USING THE SAME

Title (de)

GIESSPULVER UND DIESES VERWENDENDES STRANGGIESSVERFAHREN

Title (fr)

FLUX DE COULÉE ET PROCÉDÉ DE COULÉE CONTINUE L'UTILISANT

Publication

**EP 2035169 A4 20090930 (EN)**

Application

**EP 07747064 A 20070622**

Priority

- KR 2007003032 W 20070622
- KR 20060056509 A 20060622
- KR 20060056510 A 20060622

Abstract (en)

[origin: WO2007148939A1] A mold flux including 20 to 50 wt% of CaO, 20 to 50 wt% of SiO<sub>2</sub>, 20 wt% or less of Al<sub>2</sub>O<sub>3</sub>, 20 wt% or less of Na<sub>2</sub>O, 10 wt% or less of Li<sub>2</sub>O, 20 wt% or less of B<sub>2</sub>O<sub>3</sub>, and 10 wt% or less of MgO, and a continuous casting method using the mold flux. The quality of products can be improved, since the occurrence of surface cracks of cast pieces is suppressed. Further, since the occurrence of break-out is prevented, it is possible to improve the process stability.

IPC 8 full level

**B22D 11/108** (2006.01)

CPC (source: EP)

**B22D 11/111** (2013.01)

Citation (search report)

- [X] KR 20020052121 A 20020702 - POSCO [KR]
- [X] JP H07185755 A 19950725 - KAWASAKI STEEL CO
- [X] AUTORENkollektiv: "Slag Atlas 2nd Edition", 1995, VERLAG STAHLLEISEN GMBH, XP002538735
- See references of WO 2007148939A1

Designated contracting state (EPC)

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

DOCDB simple family (publication)

**WO 2007148939 A1 20071227**; EP 2035169 A1 20090318; EP 2035169 A4 20090930; EP 2035169 B1 20170315; JP 2009541060 A 20091126; JP 5037612 B2 20121003

DOCDB simple family (application)

**KR 2007003032 W 20070622**; EP 07747064 A 20070622; JP 2009516406 A 20070622