

Title (en)
FALSE TWIST YARN AND PROCESS FOR PRODUCING THE SAME

Title (de)
FALSCHDRAHTZWIRN UND HERSTELLUNGSVERFAHREN DAFÜR

Title (fr)
FIL MOUSSE FAUSSE TORSION ET SON PROCÉDÉ DE PRODUCTION

Publication
EP 2042627 B1 20121017 (EN)

Application
EP 07790586 A 20070711

Priority

- JP 2007063782 W 20070711
- JP 2006191265 A 20060712

Abstract (en)
[origin: EP2042627A1] A false twisting yam composed of monofilaments containing a polyester component of which main component is polytrimethylene terephthalate, wherein said false twisting yam is a false twisting yam which satisfies all of the requirements of (1) a shrinkage ratio by wet heat treatment at 98°C for 20 minutes is 5% or less, (2) A ratio (TS/WS) of elastic stretch ratio after wet heat treatment at 90°C for 20 minutes (WS) and elastic stretch ratio after dry heat treatment at 90°C for 15 minutes (TS) is, $0 < TS/WS \leq 1$, and (3) a tensile strength is 2.0 cN/dtex or more. By using the false twisting yam of the present invention, it is possible to produce a pile cloth having a soft touch and a low shrinkage.

IPC 8 full level
D02G 1/02 (2006.01); **D02G 1/06** (2006.01); **D03D 27/00** (2006.01)

CPC (source: EP US)
D02G 1/02 (2013.01 - EP US); **D02G 1/06** (2013.01 - EP US)

Citation (examination)
US 2003052436 A1 20030320 - KOYANAGI TADASHI [JP], et al

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

DOCDB simple family (publication)
EP 2042627 A1 20090401; **EP 2042627 A4 20100602**; **EP 2042627 B1 20121017**; CN 101490323 A 20090722; CN 101490323 B 20110316; ES 2396158 T3 20130219; PL 2042627 T3 20130329; PT 2042627 E 20130114; US 2009199533 A1 20090813; US 7958714 B2 20110614; WO 2008007682 A1 20080117

DOCDB simple family (application)
EP 07790586 A 20070711; CN 200780026150 A 20070711; ES 07790586 T 20070711; JP 2007063782 W 20070711; PL 07790586 T 20070711; PT 07790586 T 20070711; US 37307307 A 20070711