

Title (en)

Method for hardening stainless steel surfaces on workpieces and fused salt for performing the method

Title (de)

Verfahren zum Härten von Oberflächen von Werkstücken aus Edelstahl und Salzschnmelze zur Durchführung des Verfahrens

Title (fr)

Procédé destiné au durcissement de surfaces de pièces usinées en acier inoxydable et sels fondus pour l'exécution du procédé

Publication

EP 2055801 B1 20121205 (DE)

Application

EP 08018519 A 20081023

Priority

DE 102007051949 A 20071031

Abstract (en)

[origin: CA2642322A1] A method for hardening the surfaces of work pieces made from stainless steel includes submerging the work pieces into a molten salt bath having the composition: potassium acetate 60 - 100 weight %; sodium acetate 0 - 100 weight %; metal salt 0 - 2 weight %, and are subjecting the work pieces to the molten salt bath for a period of 24 to 240 hours, during which the temperature of the molten salt bath is maintained less than 400.degree. C.

IPC 8 full level

C23C 8/46 (2006.01)

CPC (source: EP US)

C21D 1/46 (2013.01 - EP US); **C23C 8/46** (2013.01 - EP US); **C23C 10/24** (2013.01 - EP US); **C21D 2211/001** (2013.01 - EP US)

Designated contracting state (EPC)

BE DE DK FR IT LU NL

DOCDB simple family (publication)

DE 102007051949 B3 20090312; CA 2642322 A1 20090430; DK 2055801 T3 20130128; EP 2055801 A1 20090506; EP 2055801 B1 20121205; JP 2009108411 A 20090521; JP 5371376 B2 20131218; US 2010108198 A1 20100506; US 8083866 B2 20111227

DOCDB simple family (application)

DE 102007051949 A 20071031; CA 2642322 A 20081029; DK 08018519 T 20081023; EP 08018519 A 20081023; JP 2008279150 A 20081030; US 26296008 A 20081031