

Title (en)  
METHOD FOR THE CONTINUOUS PRODUCTION OF DISPERSIONS IN A VORTEX REACTOR

Title (de)  
VERFAHREN ZUR KONTINUIERLICHEN HERSTELLUNG VON DISPERSIONEN IN EINEM WIRBELKAMMERREAKTOR

Title (fr)  
PROCÉDÉ DE PRODUCTION CONTINUE DE DISPERSIONS DANS UN RÉACTEUR À CHAMBRE DE TURBULENCE

Publication  
**EP 2091639 A1 20090826 (DE)**

Application  
**EP 07818529 A 20070928**

Priority  
• EP 2007008446 W 20070928  
• DE 102006053497 A 20061114

Abstract (en)  
[origin: WO2008058593A1] The invention relates to a method for the continuous production of stable dispersions, containing dispersed particles with a particle size  $d < 50 \mu\text{m}$  of at least 1 micrometre, in a concentration of between 1 and 70 % by weight, in relation to the total weight of the dispersion. Said method is characterised in that: a) a component to be dispersed (disperse phase) in liquid form is continuously metered through a nozzle at a temperature of between 10 and 350°C and a pressure of between 1 and 2,000 bar via a first inlet into a vortex reactor with a vortex chamber volume of between 0.1 and 100 ml, by means of a control valve, extruder and/or pump; b) a dispersant (continuous phase) is continuously metered via a second inlet into the vortex reactor at a pressure of between 1 and 2,000 bar and a temperature of between 10 and 350°C; c) one or more dispersing agents are either added to the disperse phase and mixed and/or are added to the continuous phase and mixed and/or are continuously metered via a third inlet into the vortex reactor at a pressure of between 1 and 2,000 bar and a temperature ranging between 10 and 350°C; d) the mixture obtained as per steps a) to c) remains for between 0.001 second and 10 minutes in the vortex reactor and optionally in a holding module, which maintains the temperature of the mixture obtained as per steps a) to c) at a constant level; and e) the dispersion produced in step d) is introduced into one or more heat exchangers and is cooled to a temperature of between 10 and 250°C over a period lasting between 0.001 second and 10 minutes.

IPC 8 full level  
**B01F 3/08** (2006.01); **B01F 5/00** (2006.01)

CPC (source: EP)  
**B01F 23/4105** (2022.01); **B01F 23/56** (2022.01); **B01F 25/10** (2022.01); **B01F 25/25** (2022.01)

Citation (search report)  
See references of WO 2008058593A1

Designated contracting state (EPC)  
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

DOCDB simple family (publication)  
**DE 102006053497 A1 20080515**; EP 2091639 A1 20090826; WO 2008058593 A1 20080522

DOCDB simple family (application)  
**DE 102006053497 A 20061114**; EP 07818529 A 20070928; EP 2007008446 W 20070928