

Title (en)  
METHOD OF FORMING HIGH STRENGTH L12 ALUMINIUM ALLOYS

Title (de)  
VERFAHREN ZUR HERSTELLUNG VON L12-ALUMINIUMLEGIERUNGEN MIT HOHER FESTIGKEIT

Title (fr)  
PROCÉDÉ DE FABRICATION D'ALLIAGES D'ALUMINIUM L12 À HAUTE RÉSISTANCE

Publication  
**EP 2112244 A1 20091028 (EN)**

Application  
**EP 09251028 A 20090331**

Priority  
US 14838708 A 20080418

Abstract (en)  
High temperature heat treatable aluminum alloys that can be used at temperatures from about -420°F (-251°C) up to about 650°F (343°C) are described. The alloys are strengthened by dispersion of particles based on the L1 2 intermetallic compound Al<sub>3</sub>X. These alloys comprise aluminum, zinc, magnesium, at least one of scandium, erbium, thulium, ytterbium, and lutetium; and at least one of gadolinium, yttrium, zirconium, titanium, hafnium, and niobium. Copper is an optional alloying element.

IPC 8 full level  
**C22C 21/10** (2006.01); **C22F 1/053** (2006.01)

CPC (source: EP US)  
**C22C 21/10** (2013.01 - EP US); **C22F 1/053** (2013.01 - EP US)

Citation (applicant)

- US 6248453 B1 20010619 - WATSON THOMAS J [US]
- US 2006269437 A1 20061130 - PANDEY AWADH B [US]
- WO 9532074 A2 19951130 - ASHURST CORP [US]
- JP H09279284 A 19971028 - FURUKAWA ELECTRIC CO LTD
- US 2001054247 A1 20011227 - STALL THOMAS C [US], et al
- US 5055257 A 19911008 - CHAKRABARTI DHRUBA J [US], et al
- WO 03085146 A1 20031016 - PECHINEY RHENALU [FR], et al
- WO 03085145 A2 20031016 - PECHINEY RHENALU [FR], et al
- US 2008066833 A1 20080320 - LIN JEN C [US], et al
- WO 2004046402 A2 20040603 - UNIVERSAL ALLOY CORP [US]
- WO 9610099 A1 19960404 - ASHURST TECHNOLOGY CORP IRELAN [IE]
- RIDDLE, YANCY W. ET AL.: "Recrystallization performance of AA7050 varied with Sc and Zr", MATERIALS SCIENCE FORUM, vol. 331, no. 337, pages 799 - 804
- MIL'MAN, YU V. ET AL.: "Effect of additional alloying with transition metals on the structure of an Al-7.1 Zn-1.3 Mg-0.12 Zr alloy", METALLOFIZIKA I NOVEISHIE TEKHNOLOGII, vol. 26, no. 10, pages 1363 - 1378, XP009117293

Citation (search report)

- [X] WO 9532074 A2 19951130 - ASHURST CORP [US]
- [X] WO 9610099 A1 19960404 - ASHURST TECHNOLOGY CORP IRELAN [IE]
- [X] JP H09279284 A 19971028 - FURUKAWA ELECTRIC CO LTD
- [X] US 2001054247 A1 20011227 - STALL THOMAS C [US], et al
- [X] US 5055257 A 19911008 - CHAKRABARTI DHRUBA J [US], et al
- [X] WO 03085146 A1 20031016 - PECHINEY RHENALU [FR], et al
- [X] WO 03085145 A2 20031016 - PECHINEY RHENALU [FR], et al
- [X] US 2008066833 A1 20080320 - LIN JEN C [US], et al
- [X] WO 2004046402 A2 20040603 - UNIVERSAL ALLOY CORP [US]
- [A] EP 1439239 A1 20040721 - UNITED TECHNOLOGIES CORP [US]
- [A] US 2004191111 A1 20040930 - NIE ZUOREN [CN], et al
- [A] CN 1436870 A 20030820 - UNIV BEIJING POLYTECHNIC [CN]
- [X] RIDDLE, YANCY W. ET AL: "Recrystallization performance of AA7050 varied with Sc and Zr", MATERIALS SCIENCE FORUM , 331-337(Pt. 2, ALLUMINIUM ALLOYS: THEIR PHYSICAL AND MECHANICAL PROPERTIES), 799-804 CODEN: MSFOEP; ISSN: 0255-5476, 2000, XP009117290
- [X] MIL'MAN, YU. V. ET AL: "Effect of additional alloying with transition metals on the structure of an Al-7.1 Zn-1.3 Mg-0.12 Zr alloy", METALLOFIZIKA I NOVEISHIE TEKHNOLOGII , 26(10), 1363-1378 CODEN: MNTEEU; ISSN: 1024-1809, 2004, XP009117293

Cited by  
CN110791688A; CN107447140A; CN104004945A; CN107447144A; EP2251447A1; US10199522B2; EP2871642B1

Designated contracting state (EPC)  
DE GB

Designated extension state (EPC)  
AL BA RS

DOCDB simple family (publication)  
**EP 2112244 A1 20091028; EP 2112244 B1 20190501**; US 2009263273 A1 20091022

DOCDB simple family (application)  
**EP 09251028 A 20090331**; US 14838708 A 20080418