

Title (en)
COMPOSITE GRAPHITE PARTICLES FOR NON-AQUEOUS SECONDARY BATTERIES, NEGATIVE ELECTRODE MATERIAL CONTAINING THE SAME, NEGATIVE ELECTRODES, AND NON-AQUEOUS SECONDARY BATTERIES

Title (de)
VERBUND-GRAPHITTEILCHEN FÜR WASSERFREIE SEKUNDÄRBATTERIEN, DIESE ENTHALTENDES NEGATIV-ELEKTRODENMATERIAL, NEGATIV-ELEKTRODEN UND WASSERFREIE SEKUNDÄRBATTERIEN

Title (fr)
PARTICULES DE GRAPHITE COMPOSITES POUR DES BATTERIES SECONDAIRES NON AQUEUSES, MATÉRIAU D'ÉLECTRODE NÉGATIVE CONTENANT CELLES-CI, ÉLECTRODES NÉGATIVES ET BATTERIES SECONDAIRES NON AQUEUSES

Publication
EP 2128916 A1 20091202 (EN)

Application
EP 07860084 A 20071225

Priority
• JP 2007074855 W 20071225
• JP 2006348703 A 20061226

Abstract (en)
A subject is to provide a nonaqueous secondary battery which is sufficiently low in charge/discharge irreversible capacity in initial cycling even when an active-material layer comprising a negative-electrode material and formed on a current collector has been densified for capacity increase. The subject has been accomplished with composite graphite particles for a nonaqueous secondary battery which comprise a composite of spherical graphite particles and a binder graphite and which at least satisfy any requirement selected from the group consisting of the following requirements (a) to (g): (a) the composite graphite particles include composite graphite particles in which at least part of the spherical graphite particles is exposed at the surface thereof; (b) the composite graphite particles include composite graphite particles which have an imperfect laminate structure of the spherical graphite particles near the surface thereof; (c) when the median diameter of the spherical graphite particles and the median diameter of the composite graphite particles are expressed by a and b, respectively, then the ratio $c=a/b$ is 0.93 or larger; (d) the composite graphite particles have a Raman R value of 0.15-0.25, an average degree of circularity of 0.85 or higher, a tap density of 0.87-1.25 g/cm³, and a BET specific surface area of 2.5-8 m²/g; (e) a volume of 0.01-2 μm pores as measured with a mercury porosimeter, is 0.05-1 mL/g; (f) the amount of CO groups present on the surface normalized with the BET specific surface area is 1.15-5 μmol/m²; and (g) when an electrode is produced by preparing a slurry using the composite graphite particles and a specific electrolytic solution is dropped onto the electrode, then the average time period required for the electrolytic solution to disappear completely from the electrode surface is 180 seconds or shorter.

IPC 8 full level
H01M 4/02 (2006.01); **H01M 4/133** (2010.01); **H01M 4/1393** (2010.01); **H01M 4/36** (2006.01); **H01M 4/58** (2006.01); **H01M 4/587** (2010.01); **H01M 4/62** (2006.01)

CPC (source: EP KR US)
H01M 4/02 (2013.01 - KR); **H01M 4/1393** (2013.01 - EP US); **H01M 4/58** (2013.01 - KR); **H01M 4/587** (2013.01 - EP US); **H01M 10/05** (2013.01 - KR); **H01M 2004/021** (2013.01 - EP US); **Y02E 60/10** (2013.01 - EP)

Cited by
CN109148836A; CN110137442A; US9065059B2; WO2011137508A1

Designated contracting state (EPC)
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

DOCDB simple family (publication)
EP 2128916 A1 20091202; **EP 2128916 A4 20161130**; CN 101589492 A 20091125; CN 101589492 B 20120613; JP 2008181870 A 20080807; JP 5268018 B2 20130821; KR 101441712 B1 20140917; KR 20090094818 A 20090908; US 2010086856 A1 20100408; US 8431270 B2 20130430; WO 2008084675 A1 20080717

DOCDB simple family (application)
EP 07860084 A 20071225; CN 200780047592 A 20071225; JP 2007074855 W 20071225; JP 2007332689 A 20071225; KR 20097011942 A 20071225; US 52137207 A 20071225